
JBLM DESIGN STANDARDS

DIVISION 09

FINISHES

SECTION 09 90 00

PAINTS AND COATINGS

07/20

PART 1 GENERAL

1.1 REFERENCES

The publications listed below form a part of this specification to the extent referenced. The publications are referred to within the text by the basic designation only.

AMERICAN CONFERENCE OF GOVERNMENTAL INDUSTRIAL HYGIENISTS (ACGIH)

ACGIH 0100 (2015; Suppl 2002-2016) Documentation of the Threshold Limit Values and Biological Exposure Indices

AMERICAN SOCIETY OF MECHANICAL ENGINEERS (ASME)

ASME A13.1 (2015) Scheme for the Identification of Piping Systems

ASTM INTERNATIONAL (ASTM)

ASTM C920 (2018) Standard Specification for Elastomeric Joint Sealants

ASTM D235 (2002; R 2012) Mineral Spirits (Petroleum Spirits) (Hydrocarbon Dry Cleaning Solvent)

ASTM D523 (2014; R 2018) Standard Test Method for Specular Gloss

ASTM D2824/D2824M (2018) Standard Specification for Aluminum-Pigmented Asphalt Roof Coatings, Non-Fibered, and Fibered without Asbestos

ASTM D4214 (2007; R 2015) Standard Test Method for Evaluating the Degree of Chalking of Exterior Paint Films

ASTM D4263 (1983; R 2018) Standard Test Method for Indicating Moisture in Concrete by the Plastic Sheet Method

- ASTM D4444 (2013; R 2018) Standard Test Method for Laboratory Standardization and Calibration of Hand-Held Moisture Meters
- ASTM D6386 (2016) Standard Practice for Preparation of Zinc (Hot-Dip Galvanized) Coated Iron and Steel Product and Hardware Surfaces for Painting
- ASTM F1869 (2016) Standard Test Method for Measuring Moisture Vapor Emission Rate of Concrete Subfloor Using Anhydrous Calcium Chloride

MASTER PAINTERS INSTITUTE (MPI)

- MPI 1 (2012) Aluminum Paint
- MPI 2 (2012) Aluminum Heat Resistant Enamel (up to 427 C and 800 F)
- MPI 4 (2012) Interior/Exterior Latex Block Filler
- MPI 5 (2012) Primer, Exterior Alkyd Wood
- MPI 6 (2012) Primer, Exterior Latex Wood
- MPI 7 (Oct 2009) Exterior Oil Wood Primer
- MPI 8 (2012) Alkyd, Exterior Flat (MPI Gloss Level I)
- MPI 9 (2012) Alkyd, Exterior Gloss (MPI Gloss Level 6)
- MPI 10 (2012) Latex, Exterior Flat (MPI Gloss Level 1)
- MPI 11 (2012) Latex, Exterior Semi-Gloss, MPI Gloss Level 5
- MPI 13 (2012) Stain, Exterior Solvent-Based, Semi-Transparent
- MPI 16 (2012) Stain, Exterior, Water Based, Solid Hide
- MPI 19 (2012) Primer, Zinc Rich, Inorganic
- MPI 21 (2012) Heat Resistant Coating, (Up to 205°C/402°F), MPI Gloss Level 6
- MPI 22 (2012) Aluminum Paint, High Heat (up to 590° C/1100° F)
- MPI 23 (2012) Primer, Metal, Surface Tolerant
- MPI 26 (2012) Primer, Galvanized Metal, Cementitious

MPI 27 (2012) Floor Enamel, Alkyd, Gloss (MPI Gloss Level 6)

MPI 31 (2012) Varnish, Polyurethane, Moisture Cured, Gloss (MPI Gloss Level 6)

MPI 39 (2012) Primer, Latex, for Interior Wood

MPI 42 (2012) Textured Coating, Latex, Flat

MPI 44 (2012) Latex, Interior, (MPI Gloss Level 2)

MPI 45 (2012) Primer Sealer, Interior Alkyd

MPI 46 (2012) Undercoat, Enamel, Interior

MPI 47 (2012) Alkyd, Interior, Semi-Gloss (MPI Gloss Level 5)

MPI 48 (2012) Alkyd, Interior, Gloss (MPI Gloss Level 6-7)

MPI 49 (2012) Alkyd, Interior, Flat (MPI Gloss Level 1)

MPI 50 (2012) Primer Sealer, Latex, Interior

MPI 51 (2012) Alkyd, Interior, (MPI Gloss Level 3)2

MPI 52 (2012) Latex, Interior, (MPI Gloss Level 3)

MPI 54 (2012) Latex, Interior, Semi-Gloss (MPI Gloss Level 5)

MPI 56 (2012) Varnish, Interior, Polyurethane, Oil Modified, Gloss

MPI 57 (2012) Varnish, Interior, Polyurethane, Oil Modified, Satin

MPI 59 (2012) Floor Paint, Alkyd, Low Gloss

MPI 60 (2012) Floor Paint, Latex, Low Gloss

MPI 68 (2012) Floor Paint, Latex, Gloss

MPI 71 (2012) Varnish, Polyurethane, Moisture Cured, Flat (MPI Gloss Level 1)

MPI 72 (2012) Polyurethane, Two-Component, Pigmented, Gloss (MPI Gloss Level 6-7)

MPI 77 (2012) Epoxy, Gloss

MPI 79 (2012) Primer, Alkyd, Anti-Corrosive for Metal

MPI 90 (2012) Stain, Semi-Transparent, for Interior Wood

MPI 94 (2012) Alkyd, Exterior, Semi-Gloss (MPI Gloss Level 5)

MPI 95 (2012) Primer, Quick Dry, for Aluminum

MPI 101 (2012) Primer, Epoxy, Anti-Corrosive, for Metal

MPI 107 (2012) Primer, Rust-Inhibitive, Water Based

MPI 108 (2012) Epoxy, High Build, Low Gloss

MPI 113 (2012) Elastomeric, Pigmented, Exterior, Water Based, Flat

MPI 116 (2012) Block Filler, Epoxy

MPI 119 (2012) Latex, Exterior, Gloss (MPI Gloss Level 6)

MPI 134 (2012) Primer, Galvanized, Water Based

MPI 138 (2012) Latex, Interior, High Performance Architectural, (MPI Gloss Level 2)

MPI 139 (2012) Latex, Interior, High Performance Architectural, (MPI Gloss Level 3)

MPI 140 (2012) Latex, Interior, High Performance Architectural, (MPI Gloss Level 4)

MPI 141 (2012) Latex, Interior, High Performance Architectural, Semi-Gloss (MPI Gloss Level 5)

MPI 144 (2012) Latex, Interior, Institutional Low Odor/VOC, (MPI Gloss Level 2)

MPI 145 (2012) Latex, Interior, Institutional Low Odor/VOC, (MPI Gloss Level 3)

MPI 146 (2012) Latex, Interior, Institutional Low Odor/VOC, (MPI Gloss Level 4)

MPI 147 (May 2016) Latex, Interior, Institutional Low Odor/VOC, Semi-Gloss (MPI Gloss Level 5)

MPI 151 (2012) Light Industrial Coating, Interior, Water Based (MPI Gloss Level 3)

MPI 153 (2012) Light Industrial Coating, Interior, Water Based, Semi-Gloss (MPI Gloss Level 5)

MPI 154 (2012) Light Industrial Coating, Interior, Water Based, Gloss (MPI Gloss Level 6)

MPI 161 (2012) Light Industrial Coating, Exterior, Water Based (MPI Gloss Level 3)

MPI 163 (2012) Light Industrial Coating, Exterior, Water Based, Semi-Gloss (MPI Gloss Level 5)

MPI 164 (2012) Light Industrial Coating, Exterior, Water Based, Gloss (MPI Gloss Level 6)

SCIENTIFIC CERTIFICATION SYSTEMS (SCS)

SCS SCS Global Services (SCS) Indoor Advantage

SOCIETY FOR PROTECTIVE COATINGS (SSPC)

SSPC 7/NACE No.4 (2007; E 2004) Brush-Off Blast Cleaning

SSPC Guide 6 (2015) Guide for Containing Surface Preparation Debris Generated During Paint Removal Operations

SSPC Guide 7 (2004; E 2004) Guide to the Disposal of Lead-Contaminated Surface Preparation Debris

SSPC PA 1 (2016) Shop, Field, and Maintenance Coating of Metals

SSPC PA Guide 3 (1982; E 1995) A Guide to Safety in Paint Application

SSPC Paint 18 (1982; E 2004) Chlorinated Rubber Intermediate Coat Paint

SSPC QP 1 (2019) Standard Procedure for Evaluating Painting Contractors (Field Application to Complex Industrial Structures)

SSPC SP 1 (2015) Solvent Cleaning

SSPC SP 2 (1982; E 2000; E 2004) Hand Tool Cleaning

SSPC SP 3 (1982; E 2004) Power Tool Cleaning

SSPC SP 6/NACE No.3 (2007) Commercial Blast Cleaning

SSPC SP 10/NACE No. 2 (2007) Near-White Blast Cleaning

SSPC SP 12/NACE No.5 (2002) Surface Preparation and Cleaning of Metals by Waterjetting Prior to Recoating

SSPC VIS 1 (2002; E 2004) Guide and Reference Photographs for Steel Surfaces Prepared by Dry Abrasive Blast Cleaning

SSPC VIS 3 (2004) Guide and Reference Photographs for Steel Surfaces Prepared by Hand and Power Tool Cleaning

SSPC VIS 4/NACE VIS 7 (1998; E 2000; E 2004) Guide and Reference Photographs for Steel Surfaces Prepared by Waterjetting

SOCIETY OF AUTOMOTIVE ENGINEERS INTERNATIONAL (SAE)

SAE AMS-STD-595A (2017) Colors used in Government Procurement

U.S. ARMY CORPS OF ENGINEERS (USACE)

EM 385-1-1 (2014) Safety and Health Requirements Manual

U.S. DEPARTMENT OF DEFENSE (DOD)

MIL-PRF-680 (2010; Rev C; Notice 1 2015) Degreasing Solvent

MIL-STD-101 (2014; Rev C) Color Code for Pipelines and for Compressed Gas Cylinders

U.S. ENVIRONMENTAL PROTECTION AGENCY (EPA)

EPA Method 24 (2000) Determination of Volatile Matter Content, Water Content, Density, Volume Solids, and Weight Solids of Surface Coatings

U.S. FEDERAL AVIATION ADMINISTRATION (FAA)

FAA AC 70/7460-1 (2015; Rev L) Obstruction Marking and Lighting

U.S. GENERAL SERVICES ADMINISTRATION (GSA)

FED-STD-313 (2014; Rev E) Material Safety Data, Transportation Data and Disposal Data for Hazardous Materials Furnished to Government Activities

U.S. NATIONAL ARCHIVES AND RECORDS ADMINISTRATION (NARA)

29 CFR 1910.1000 Air Contaminants

29 CFR 1910.1001 Asbestos

29 CFR 1910.1025 Lead

29 CFR 1926.62 Lead

UNDERWRITERS LABORATORIES (UL)

1.2 SUBMITTALS

Government approval is required for submittals with a "G" designation; submittals not having a "G" designation are [for Contractor Quality Control approval.][for information only. When used, a designation following the "G" designation identifies the office that will review the submittal for the Government.] Submittals with an "S" are for inclusion in the [Sustainability eNotebook, in conformance with Section 01 33 29 SUSTAINABILITY REPORTING][Environmental Records Binder, in conformance with Section 01 57 19.01 20 SUPPLEMENTAL TEMPORARY ENVIRONMENTAL CONTROLS]. Submit the following in accordance with Section 01 33 00 SUBMITTAL PROCEDURES:

The current MPI, "Approved Product List" which lists paint by brand, label, product name and product code as of the date of contract award, will be used to determine compliance with the submittal requirements of this specification. The Contractor may choose to use a subsequent MPI "Approved Product List", however, only one list may be used for the entire contract and each coating system is to be from a single manufacturer. Provide all coats on a particular substrate from a single manufacturer. No variation from the MPI Approved Products List is acceptable.

Samples of specified materials may be taken and tested for compliance with specification requirements.

SD-01 Preconstruction Submittals

[Recycled Content for Latex Paint; S]

[Biobased Content for Paint; S]

[Biobased Content for Wood Stain; S]

[Biobased Content for Wood Sealant; S]

[Biobased Content for Roof Coatings; S]

[Biobased Content for Water Tank Coatings; S]

VOC Content for Interior Paints and Coatings; S

SD-02 Shop Drawings

Piping Identification

SD-03 Product Data

Coating; G[, [____]]

Sealant

SD-04 Samples

Color; G[, [_____]]

Textured Wall Coating System; G[, [_____]]

[Sample Textured Wall Coating System Mock-Up; G[, [_____]]

]SD-07 Certificates

Applicator's Qualifications

Qualification Testing laboratory for coatings; G[, [_____]]

Indoor Air Quality for Paints and Primers

[Indoor Air Quality for Consolidated Latex Paints

]SD-08 Manufacturer's Instructions

Application Instructions

Mixing

Manufacturer's Safety Data Sheets

SD-10 Operation and Maintenance Data

Coatings; G[, [_____]]

SD-11 Closeout Submittals

[Recycled Content for Latex Paint; S]

[Biobased Content for Paint; S]

[Biobased Content for Wood Stain; S]

[Biobased Content for Wood Sealant; S]

[Biobased Content for Roof Coatings; S]

[Biobased Content for Water Tank Coatings; S]

VOC Content for Interior Paints and Coatings; S

1.3 CERTIFICATES

1.3.1 Indoor Air Quality

Submit required indoor air quality certifications in one submittal package.

1.3.1.1 Paints and Coatings

Provide paint and coating products certified to meet indoor air quality requirements by **UL 2818** (Greenguard) Gold, **SCS** Global Services Indoor Advantage Gold or provide certification by other third-party programs. Provide current product certification documentation from certification body.

1.4 APPLICATOR'S QUALIFICATIONS

[1.4.1 Contractor Qualification

Submit the name, address, telephone number, FAX number, and e-mail address of the contractor that will be performing all surface preparation and coating application. Submit evidence that key personnel have successfully performed surface preparation and application of coatings on [_____] on a minimum of three similar projects within the past three years. List information by individual and include the following:

- a. Name of individual and proposed position for this work.
- b. Information about each previous assignment including:

Position or responsibility

Employer (if other than the Contractor)

Name of facility owner

Mailing address, telephone number, and telex number (if non-US) of facility owner

Name of individual in facility owner's organization who can be contacted as a reference

Location, size and description of structure

Dates work was carried out

Description of work carried out on structure

[1.4.2 SSPC QP 1 Certification

All contractors and subcontractors that perform surface preparation or coating application must be certified by the Society for Protective Coatings (formerly Steel Structures Painting Council) (SSPC) to the requirements of **SSPC QP 1** prior to contract award, and must remain certified while accomplishing any surface preparation or coating application. If a contractor's or subcontractor's certification expires, the firm will not be allowed to perform any work until the certification is reissued. Requests for extension of time for any delay to the completion of the project due to an inactive certification will not be considered and liquidated damages will apply. Notify the Contracting Officer of any change in contractor certification status.

]1.5 QUALITY ASSURANCE

1.5.1 Field Samples and Tests

The Contracting Officer may choose up to two coatings that have been delivered to the site to be tested at no cost to the Government. Take samples of each chosen product as specified in the paragraph SAMPLING PROCEDURES. Test each chosen product as specified in the paragraph TESTING

PROCEDURE. Remove products from the job site which do not conform, and replace with new products that conform to the referenced specification. Test replacement products that failed initial testing at no cost to the Government.

[Another required testing is Batch Quality Conformance Testing to prove conformance of the manufacturer's paint to the specified MPI standard. This testing is accomplished before the materials are delivered to the job site. Provide testing for [_____] paint products. Test paint products as specified in the paragraph "Testing Procedure".

]1.5.1.1 Sampling Procedure

The Contracting Officer will select paint at random from the products that have been delivered to the job site for sample testing. The Contractor will provide **one liter (one quart)** samples of the selected paint materials. Take samples in the presence of the Contracting Officer, and label, and identify each sample. Provide labels in accordance with the paragraph PACKAGING, LABELING, AND STORAGE of this specification.

1.5.1.2 Testing Procedure

Provide Batch Quality Conformance Testing for specified products, as defined by and performed by MPI. As an alternative to Batch Quality Conformance Testing, the Contractor may provide **Qualification Testing** for specified products above to the appropriate MPI product specification, using the third-party laboratory approved under the paragraph "Qualification Testing" laboratory for coatings. Include the backup data and summary of the test results within the qualification testing lab report. Provide a summary listing of all the reference specification requirements and the result of each test. Clearly indicate in the summary whether the tested paint meets each test requirement. Note that Qualification Testing may take 4 to 6 weeks to perform, due to the extent of testing required.

Submit name, address, telephone number, FAX number, and e-mail address of the independent third party laboratory selected to perform testing of coating samples for compliance with specification requirements. Submit documentation that laboratory is regularly engaged in testing of paint samples for conformance with specifications, and that employees performing testing are qualified. If MPI is chosen to perform the Batch Quality Conformance testing, the above submittal information is not required, only a letter is required from the Contractor stating that MPI will perform the testing.

1.5.2 Textured Wall Coating System

Three complete samples of each indicated type, pattern, and color of textured wall coating system applied to a panel of the same material as that on which the coating system will be applied in the work. Provide samples of wall coating systems minimum **125 by 175 mm (5 by 7 inches)** and of sufficient size to show pattern repeat and texture.

[1.5.3 Sample Textured Wall Coating System Mock-Up

After coating samples are approved, and prior to starting installation, provide a minimum **2.43 m by 2.43 m (8 foot by 8 foot)** mock-up for each substrate and for each color and type of textured wall coating, using the

actual substrate materials. Use the approved mock-up samples as a standard of workmanship for installation within the facility. Submit at least 48 hour advance written notice to the Contracting Officer's Representative prior to mock-up installation.

1.6 REGULATORY REQUIREMENTS

1.6.1 Environmental Protection

In addition to requirements specified elsewhere for environmental protection, provide coating materials that conform to the restrictions of the local Air Pollution Control District and regional jurisdiction. Notify Contracting Officer of any paint specified herein which fails to conform.

1.6.2 Lead Content

Do not use coatings having a lead content over 0.06 percent by weight of nonvolatile content.

1.6.3 Chromate Content

Do not use coatings containing zinc-chromate or strontium-chromate.

1.6.4 Asbestos Content

Provide asbestos-free materials.

1.6.5 Mercury Content

Provide materials free of mercury or mercury compounds.

1.6.6 Silica

Provide abrasive blast media containing no free crystalline silica.

1.6.7 Human Carcinogens

Provide materials that do not contain ACGIH 0100 confirmed human carcinogens (A1) or suspected human carcinogens (A2).

1.7 PACKAGING, LABELING, AND STORAGE

Provide paints in sealed containers that legibly show the contract specification number, designation name, formula or specification number, batch number, color, quantity, date of manufacture, manufacturer's formulation number, manufacturer's directions including any warnings and special precautions, and name and address of manufacturer. Furnish pigmented paints in containers not larger than 20 liters (5 gallons). Store paints and thinners in accordance with the manufacturer's written directions and JBLM installation Regulation 200-1, and as a minimum, stored off the ground, under cover, with sufficient ventilation to prevent the buildup of flammable vapors, and at temperatures between 4 to 35 degrees C (40 to 95 degrees F). Do not store paint, polyurethane, varnish, or wood stain products with materials that have a high capacity to adsorb VOC emissions, [including [____]]. Do not store paint, polyurethane, varnish, or wood stain products in occupied spaces.

1.8 SAFETY AND HEALTH

Apply coating materials using safety methods and equipment in accordance with the following:

Comply with applicable Federal, State, and local laws and regulations, and with the ACCIDENT PREVENTION PLAN, including the Activity Hazard Analysis as specified in Section 01 35 26 GOVERNMENT SAFETY REQUIREMENTS and in Appendix A of EM 385-1-1. Include in the Activity Hazard Analysis the potential impact of painting operations on painting personnel and on others involved in and adjacent to the work zone.

1.8.1 Safety Methods Used During Coating Application

Comply with the requirements of SSPC PA Guide 3.

1.8.2 Toxic Materials

To protect personnel from overexposure to toxic materials, conform to the most stringent guidance of:

- a. The applicable manufacturer's Safety Data Sheets (SDS) or local regulation.
- b. 29 CFR 1910.1000.
- c. ACGIH 0100, threshold limit values.
- [d. Contact JBLM Directorate of Public Works (DPW) Environmental Division for the latest requirements in place for handling of lead based paint residues. For actions at JBLM Yakima Training Center (YTC), contact JBLM YTC Environmental Division. The appropriate OSHA standard in 29 CFR 1910.1025 and 29 CFR 1926.62 for surface preparation on painted surfaces containing lead. Removal and disposal of coatings which contain lead is specified in Section 02 83 00 LEAD REMEDIATION[_____]. Additional guidance is given in SSPC Guide 6 and SSPC Guide 7. Refer to drawings for list of hazardous materials located on this project. Coordinate paint preparation activities with this specification section. If Toxicity Characteristics Leaching Procedure (TCLP) analysis of paint chip samples of removed paint particles exceeds maximum allowable concentration, all solid materials that could be contaminated with solid particles of paint shall be collected and containerized in a Department of Transportation Specification 1A2 container (open-head, 55-gallon drum). Drums shall be labeled in accordance with WAC 173-303. DPW Environmental Division Operations Branch, phone 967-4786, shall be notified of any such material, storage location, and estimate of total number of drums of waste for actions on JBLM. Operations Branch will help coordinate the disposal of the material with the Contractor and Defense Logistics Agency Disposition Services-Lewis (DLA DS-L) or other agency as appropriate. The Contractor shall process drums through Operations Branch to the DLA DS-L for projects on JBLM. For actions on JBLM YTC, the Contractor must coordinate with the One Stop Yard, 509-577-3830.
- [e. The appropriate OSHA standards in 29 CFR 1910.1001 for surface preparation of painted surfaces containing asbestos. Removal and disposal of coatings which contain asbestos materials is specified in

Section 02 82 00 ASBESTOS REMEDIATION. Refer to drawings for list of hazardous materials located on this project. Coordinate paint preparation activities with this specification section.

]Submit manufacturer's Safety Data Sheets for coatings, solvents, and other potentially hazardous materials, as defined in FED-STD-313.

1.9 ENVIRONMENTAL CONDITIONS

Comply, at minimum, with manufacturer recommendations for space ventilation during and after installation.[Isolate area of application from rest of building when applying high-emission paints or coatings.]

1.9.1 Coatings

Do not apply coating when air or substrate conditions are:

- a. Less than 3 degrees C (5 degrees F) above dew point;
- b. Below 10 degrees C (50 degrees F) or over 35 degrees C (95 degrees F), unless specifically pre-approved by the Contracting Officer and the product manufacturer. Do not, under any circumstances, violate the manufacturer's application recommendations.

1.9.2 Post-Application

Vacate space for as long as possible after application. Wait a minimum of 48 hours before occupying freshly painted rooms. Maintain one of the following ventilation conditions during the curing period, or for 72 hours after application:

- a. Supply 100 percent outside air 24 hours a day.
- b. Supply airflow at a rate of 6 air changes per hour, when outside temperatures are between 13 degrees C (55 degrees F) and 29 degrees C (85 degrees F) and humidity is between 30 percent and 60 percent.
- c. Supply airflow at a rate of 1.5 air changes per hour, when outside air conditions are not within the range stipulated above.

1.10 SCHEDULING

Allow paint, polyurethane, varnish, and wood stain installations to cure prior to the installation of materials that adsorb VOCs, including [_____].

1.11 COLOR SELECTION

1.11.1 Color Coding For Shore-To-Ship Utility Connections

[Color Coding For Shore-To-Ship Utility Connections: Paint hose connection fittings and shut-off valves the designated color. In addition to color coding provide 50 mm (2 inch) high stenciled letters using black stencil paint, clearly designating service for each connection.

Color Coding for Shore-to-Ship
Utility Connections

<u>Service</u>	<u>Color</u>	<u>SAE AMS-STD-595A No.</u>
Potable Water*	Blue	15044
Water Provided for Fire Protection**	Red	11105
Chilled Water	Striped Blue/White	15044/17886
Oily Waste Water	Striped Yellow/Black	13538/17038
Sewer	Gold	17043
Steam	White	17886
High Pressure Air	Gray	16081
Low Pressure Air	Tan	10324
Fuel	Yellow	13655

* This includes connections serving domestic functions.

** This includes non-potable salt water or, at some locations, fresh water connections provided for fire protection (may also include flushing and cooling requirements). Note: This does not include waterfront fire hydrants.

]Provide colors of finish coats as indicated or specified. Allow Contracting Officer to select colors not indicated or specified. Manufacturers' names and color identification are used for the purpose of color identification only. Named products are acceptable for use only if they conform to specified requirements. Products of other manufacturers are acceptable if the colors approximate colors indicated and the product conforms to specified requirements.

Tint each coat progressively darker to enable confirmation of the number of coats.

Provide color, texture, and pattern of wall coating systems [as indicated][in accordance with Section 09 06 00 SCHEDULES FOR FINISHES] [_____].

Submit manufacturer's samples of paint colors. Cross reference color samples to color scheme as indicated. Submit color stencil codes.

1.11.2 Interior Painting of Buildings

Buildings shall be painted the following schemes. Accent colors are allowed as ordered by the Contracting Officer or their authorized representative.

1.11.2.1 Basic Colors

Authorized wall and ceiling color shall be Natural Choice-SW 7011 (eggshell finish), (Approximately equivalent to Federal Specs 27722 (matte finish)).

1.11.2.2 Accent Colors

Authorized trim color shall be Tony Taupe- SW7038 (semi-gloss finish), (Approximately equivalent to Federal Specs 26521 (semi-gloss finish). Authorized accent color shall be Grassland- SW 6163 (eggshell finish) limited use only, (Approximately Federal Specs 36595 (matte finish).

1.11.3 Exterior Painting Colors for Buildings

Refer to the JBLM Installation Design Guide for color charts. The color of paint to be used should be based on manufacturer's correspondence to the six-digit Pantone Architecture and Interior number and shall not be predicated on matching a computer-generated sample.

The name provided for the colors is a generic name representing the color range and is not the actual Pantone name for that color. Always use the six-digit Pantone A&I number instead of generic name when referencing the color.

Select colors from the exterior color list (Item 3 under Design Requirements) based upon their appropriateness to the building type, desired appearance, material to be painted and prevailing architectural design and landscape character of the installation. Ease of maintenance, and sustainability should also be considered.

1.12 LOCATION AND SURFACE TYPE TO BE PAINTED

1.12.1 Painting Included

Where a space or surface is indicated to be painted, include the following unless indicated otherwise.

- a. Surfaces behind portable objects and surface mounted articles readily detachable by removal of fasteners, such as screws and bolts.
- b. New factory finished surfaces that require identification or color coding and factory finished surfaces that are damaged during performance of the work.
- c. Existing coated surfaces that are damaged during performance of the work.

1.12.1.1 Exterior Painting

Includes new surfaces[, existing coated surfaces,] [and] [existing uncoated surfaces,] of the building[s] and appurtenances. Also included are existing coated surfaces made bare by cleaning operations.

1.12.1.2 Interior Painting

Includes new, existing coated, and existing uncoated surfaces of the buildings and appurtenances as indicated and existing coated surfaces made bare by cleaning operations. Where a space or surface is indicated to be painted, include the any exposed columns, girders, beams, joists, and metal deck; and other contiguous surfaces.

- a. Exposed columns, girders, beams, joists, and metal deck; and

- b. Other contiguous surfaces.

1.12.2 Painting Excluded

Do not paint the following unless indicated otherwise.

- a. Surfaces concealed and made inaccessible by panelboards, fixed ductwork, machinery, and equipment fixed in place.
- b. Surfaces in concealed spaces. Concealed spaces are defined as enclosed spaces above suspended ceilings, furred spaces, attic spaces, crawl spaces, elevator shafts and chases.
- c. Steel to be embedded in concrete.
- d. Copper, stainless steel, aluminum, brass, and lead except existing coated surfaces.
- e. Hardware, fittings, and other factory finished items.
- [f. Do not paint surfaces in the following areas: [_____].

]1.12.3 Mechanical and Electrical Painting

Includes field coating of [interior] [and] [exterior] new [and existing] surfaces.

- a. Where a space or surface is indicated to be painted, include the following items unless indicated otherwise.

- (1) Exposed piping, conduit, and ductwork;
- (2) Supports, hangers, air grilles, and registers;
- (3) Miscellaneous metalwork and insulation coverings.

- [b. Do not paint the following, unless indicated otherwise:

- [(1) New zinc-coated, aluminum, and copper surfaces under insulation
-] [(2) New aluminum jacket on piping
-] [(3) New interior ferrous piping under insulation.

]1.12.3.1 Fire Extinguishing Sprinkler Systems

Clean, pretreat, prime, and paint new fire extinguishing sprinkler systems including valves, piping, conduit, hangers, supports, miscellaneous metalwork, and accessories. Apply coatings to clean, dry surfaces, using clean brushes. Clean the surfaces to remove dust, dirt, rust, and loose mill scale. Immediately after cleaning, provide the metal surfaces with one coat primer per schedules. Shield sprinkler heads with protective covering while painting is in progress. Upon completion of painting, remove protective covering from sprinkler heads. Remove sprinkler heads which have been painted and replace with new sprinkler heads. Provide primed surfaces with the following:

- a. Piping in Unfinished Areas: Provide primed surfaces with one coat of red alkyd gloss enamel applied to a minimum dry film thickness of 0.025 mm (1.0 mil) in attic spaces, spaces above suspended ceilings, crawl spaces, pipe chases, mechanical equipment room, and spaces where walls or ceiling are not painted or not constructed of a prefinished material.[In lieu of red enamel finish coat, provide piping with 50 mm (2 inch) wide red enamel bands or self-adhering red plastic bands spaced at maximum of 6 meters (20 foot) intervals.]
- b. Piping in Finished Areas: Provide primed surfaces with two coats of paint to match adjacent surfaces, except provide valves and operating accessories with one coat of red alkyd gloss enamel applied to a minimum dry film thickness of 0.025 mm (1.0 mil). Provide piping with 50 mm (2 inch) wide red enamel bands or self-adhering red plastic bands spaced at maximum of 6 meters (20 foot) intervals throughout the piping systems.

]1.12.4 Exterior Painting of Site Work Items

Field coat the following items:

New Surfaces	Existing Surfaces
a. [_____]	[_____]
b. [_____]	[_____]
c. [_____]	[_____]

]1.12.5 MISCELLANEOUS PAINTING

Lettering [Building][Room Number(s)]

Provide lettering [as scheduled on the drawings] [block] [Gothic] type, [black enamel] [water-type decalcomania, finished with a protective coating of spar varnish]. Samples must be approved before application.

[Obstructions To Aviation

Paint the following obstructions to aviation in the pattern and color prescribed by FAA AC 70/7460-1: [_____]

]1.12.6 Definitions and Abbreviations

1.12.6.1 Qualification Testing

Qualification testing is the performance of all test requirements listed in the product specification. This testing is accomplished by MPI to qualify each product for the MPI Approved Product List, and may also be accomplished by Contractor's third party testing lab if an alternative to Batch Quality Conformance Testing by MPI is desired.

1.12.6.2 Batch Quality Conformance Testing

Batch quality conformance testing determines that the product provided is the same as the product qualified to the appropriate product specification. This testing must be accomplished by an MPI testing lab.

1.12.6.3 Coating

A film or thin layer applied to a base material called a substrate. A coating may be a metal, alloy, paint, or solid/liquid suspensions on various substrates (such as metals, plastics, wood, paper, leather, cloth). They may be applied by electrolysis, vapor deposition, vacuum, or mechanical means such as brushing, spraying, calendaring, and roller coating. A coating may be applied for aesthetic or protective purposes or both. The term "coating" as used herein includes emulsions, enamels, stains, varnishes, sealers, epoxies, and other coatings, whether used as primer, intermediate, or finish coat. The terms paint and coating are used interchangeably.

1.12.6.4 DFT or dft

Dry film thickness, the film thickness of the fully cured, dry paint or coating.

1.12.6.5 DSD

Degree of Surface Degradation, the MPI system of defining degree of surface degradation. Five (5) levels are generically defined under the Assessment sections in the MPI Maintenance Repainting Manual.

1.12.6.6 EPP

Environmentally Preferred Products, a standard for determining environmental preferability in support of Executive Order 13101.

1.12.6.7 EXT

MPI short term designation for an exterior coating system.

1.12.6.8 INT

MPI short term designation for an interior coating system.

1.12.6.9 micron / microns

The metric measurement for 0.001 mm or one/one-thousandth of a millimeter.

1.12.6.10 mil / mils

The English measurement for 0.001 in or one/one-thousandth of an inch, equal to 25.4 microns or 0.0254 mm.

1.12.6.11 mm

The metric measurement for millimeter, 0.001 meter or one/one-thousandth of a meter.

1.12.6.12 MPI Gloss Levels

MPI system of defining gloss. Seven (7) gloss levels (G1 to G7) are generically defined under the Evaluation sections of the MPI Manuals. Traditionally, Flat refers to G1/G2, Eggshell refers to G3, Semigloss refers to G5, and Gloss refers to G6.

Gloss levels are defined by MPI as follows:

Gloss Level	Description	Units at 60 degrees	Units at 85 degrees
G1	Matte or Flat	0 to 5	10 max
G2	Velvet	0 to 10	10 to 35
G3	Eggshell	10 to 25	10 to 35
G4	Satin	20 to 35	35 min
G5	Semi-Gloss	35 to 70	
G6	Gloss	70 to 85	
G7	High Gloss		

Gloss is tested in accordance with [ASTM D523](#). Historically, the Government has used Flat (G1 / G2), Eggshell (G3), Semi-Gloss (G5), and Gloss (G6).

1.12.6.13 MPI System Number

The MPI coating system number in each Division found in either the MPI Architectural Painting Specification Manual or the Maintenance Repainting Manual and defined as an exterior (EXT/REX) or interior system (INT/RIN). The Division number follows the CSI Master Format.

1.12.6.14 Paint

See Coating definition.

1.12.6.15 REX

MPI short term designation for an exterior coating system used in repainting projects or over existing coating systems.

1.12.6.16 RIN

MPI short term designation for an interior coating system used in repainting projects or over existing coating systems.

PART 2 PRODUCTS

2.1 MATERIALS

Provide materials and documentation in conformance with the requirements at Section [01 33 29 SUSTAINABILITY REPORTING][01 57 19.0 20 SUPPLEMENTAL TEMPORARY ENVIRONMENTAL CONTROLS] paragraph RECYCLED CONTENT or BIO-BASED PRODUCTS.

For interior products (to be used within the building weatherproofing), provide materials and documentation in conformance with the requirements at Section [01 33 29 SUSTAINABILITY REPORTING][01 57 19.0 20 SUPPLEMENTAL TEMPORARY ENVIRONMENTAL CONTROLS] paragraph REDUCE VOLATILE ORGANIC COMPOUNDS (VOC) (LOW EMITTING MATERIALS).

See <https://sftool.gov/greenprocurement/green-products/3/building-finishes/1338/paint/0?addon=False> for more information.

Conform to the [coating](#) specifications and standards referenced in PART 3. Submit product data sheets for specified [coatings](#) and solvents. Provide preprinted cleaning and maintenance instructions for all coating systems.

Submit Manufacturer's Instructions on Mixing: Detailed mixing instructions, minimum and maximum application temperature and humidity, potlife, and curing and drying times between coats.

Provide certification of [Indoor Air Quality for paints and primers](#).

[Provide certification of [Indoor Air Quality for consolidated latex paints](#).

]PART 3 EXECUTION

3.1 PROTECTION OF AREAS AND SPACES NOT TO BE PAINTED

Prior to surface preparation and coating applications, remove, mask, or otherwise protect hardware, hardware accessories, machined surfaces, radiator covers, plates, lighting fixtures, public and private property, and other such items not to be coated that are in contact with surfaces to be coated. Following completion of painting, reinstall removed items by workmen skilled in the trades. Restore surfaces contaminated by coating materials, to original condition and repair damaged items.

[3.2 REPUTTYING AND REGLAZING

Remove cracked, loose, and defective putty or glazing compound on glazed sash and provide new putty or glazing compound. Where defective putty or glazing compound constitutes 30 percent or more of the putty at any one light, remove the glass and putty or glazing compound and reset the glass. Remove putty or glazing compound without damaging sash or glass. Clean rabbets to bare wood or metal and prime prior to reglazing. Provide linseed oil putty for wood sash. Patch surfaces to provide smooth transition between existing and new surfaces. Finish putty or glazing compound to a neat and true bead. Allow glazing compound time to cure, in accordance with manufacturer's recommendation, prior to coating application. Allow putty to set one week prior to coating application.

] [3.3 RESEALING OF EXISTING EXTERIOR JOINTS

3.3.1 Surface Condition

Begin with surfaces that are clean, dry to the touch, and free from frost and moisture; remove grease, oil, wax, lacquer, paint, defective backstop, or other foreign matter that would prevent or impair adhesion. Where adequate grooves have not been provided, clean out to a depth of [13 mm \(1/2 inch\)](#) and grind to a minimum width of [6 mm \(1/4 inch\)](#) without damage to adjoining work. Grinding is not required on metal surfaces.

3.3.2 Backstops

In joints more than [13 mm \(1/2 inch\)](#) deep, install glass fiber roving or neoprene, butyl, polyurethane, or polyethylene foams free of oil or other

staining elements as recommended by sealant manufacturer. Provide backstop material compatible with sealant. Do not use oakum and other types of absorptive materials as backstops.

3.3.3 Primer and Bond Breaker

Install the type recommended by the sealant manufacturer.

3.3.4 Ambient Temperature

Between 4 degrees C (38 degrees F) and 35 degrees C (95 degrees F) when applying sealant.

3.3.5 Exterior Sealant

For joints in vertical surfaces, provide ASTM C920, Type S or M, Grade NS, Class 25, Use NT. For joints in horizontal surfaces, provide ASTM C920, Type S or M, Grade P, Class 25, Use T. Color(s) will be selected by the Contracting Officer. Apply the sealant in accordance with the manufacturer's printed instructions. Force sealant into joints with sufficient pressure to fill the joints solidly. Apply sealant uniformly smooth and free of wrinkles.

3.3.6 Cleaning

Immediately remove fresh sealant from adjacent areas using a solvent recommended by the sealant manufacturer. Upon completion of sealant application, remove remaining smears and stains and leave the work in a clean condition. Allow sealant time to cure, in accordance with manufacturer's recommendations, prior to coating.

]3.4 SURFACE PREPARATION

Remove dirt, splinters, loose particles, grease, oil, [disintegrated coatings,] and other foreign matter and substances deleterious to coating performance as specified for each substrate before application of paint or surface treatments. Remove oil and grease prior to mechanical cleaning. Schedule cleaning so that dust and other contaminants will not fall on wet, newly painted surfaces. Spot-prime exposed ferrous metals such as nail heads on or in contact with surfaces to be painted with water-thinned paints, with a suitable corrosion-inhibitive primer capable of preventing flash rusting and compatible with the coating specified for the adjacent areas.

[3.4.1 Additional Requirements for Preparation of Surfaces With Existing Coatings

Before application of coatings, perform the following on surfaces covered by soundly-adhered coatings, defined as those which cannot be removed with a putty knife:

- a. Test existing finishes for lead before sanding, scraping, or removing. If lead is present, refer to paragraph Toxic Materials.
- b. Wipe previously painted surfaces to receive solvent-based coatings, except stucco and similarly rough surfaces clean with a clean, dry cloth saturated with mineral spirits, ASTM D235. Allow surface to dry.

Wipe immediately preceding the application of the first coat of any coating, unless specified otherwise.

- c. Sand existing glossy surfaces to be painted to reduce gloss. Brush, and wipe clean with a damp cloth to remove dust.
- d. The requirements specified are minimum. Comply also with the [application instructions](#) of the paint manufacturer.
- e. Thoroughly clean previously painted surfaces [specified to be repainted] [damaged during construction] of all grease, dirt, dust or other foreign matter.
- f. Remove blistering, cracking, flaking and peeling or otherwise deteriorated coatings.
- g. Remove chalk so that when tested in accordance with [ASTM D4214](#), the chalk resistance rating is no less than 8.
- h. Roughen slick surfaces. Repair damaged areas such as, but not limited to, nail holes, cracks, chips, and spalls with suitable material to match adjacent undamaged areas.
- i. Feather and sand smooth edges of chipped paint.
- j. Clean rusty metal surfaces as per SSPC requirements. Use solvent, mechanical, or chemical cleaning methods to provide surfaces suitable for painting.
- k. Provide new, proposed coatings that are compatible with existing coatings.

][3.4.2 Existing Coated Surfaces with Minor Defects

[Sand, spackle, and treat minor defects to render them smooth. Minor defects are defined as scratches, nicks, cracks, gouges, spalls, alligating, chalking, and irregularities due to partial peeling of previous coatings.][Remove chalking by sanding [or blasting] so that when tested in accordance with [ASTM D4214](#), the chalk rating is not less than 8.]

][3.4.3 Removal of Existing Coatings

Remove existing coatings from the following surfaces:

- a. Surfaces containing large areas of minor defects;
- b. Surfaces containing more than 20 percent peeling area; and
- c. Surfaces designated by the Contracting Officer, such as surfaces where rust shows through existing coatings.

][3.4.4 Substrate Repair

- a. Repair substrate surface damaged during coating removal;

- b. Sand edges of adjacent soundly-adhered existing coatings so they are tapered as smooth as practical to areas involved with coating removal; and
- c. Clean and prime the substrate as specified.

3.5 PREPARATION OF METAL SURFACES

3.5.1 Existing and New Ferrous Surfaces

Ferrous Surface Preparation

SSPC Blasting/Cleaning Levels^a - Primer Types/Exposures

	Exposure ^b		
	Mild	Moderate	Severe ^c
Primer Type	alkyd/oil latex oleoresinous phenolic	alkyd/oil latex oleoresinous phenolic	epoxy silicone inorganic zinc-rich
Surface Condition			
Uncoated			
Oil, grease, dirt	SP 1	for all moderate conditions, select from "mild" or "severe" for	SP 10, SP 12 WJ2 or SP 5 SP 12 WJ1
Localized corrosion - mill scale, rust	SP 2, SP 3, or SP 7 SP 12 WJ-4	intended performance level	AS ABOVE
Extensive deterioration	SP 6 ^d SP 12 WJ-3		AS ABOVE
Shop coated			
Oil, grease, dirt	^e		AS ABOVE
Localized damage to be spot repaired	SP 2, SP 3, or SP 7, SP 12 WJ-4		AS ABOVE
Extensive deterioration	SP 6 ^d , SP 12 WJ-3		AS ABOVE
Existing coating			
Oil, grease	^e	^e	SP 1
Chalking, foreign matter	^f		^g

other than
oil or grease,
localized
deterioration

Extensive
deterioration

SP 6^d, SP 12 WJ-3

SP 10,
SP 12 WJ2
or SP 5
SP 12 WJ1

^a If it is not possible to abrasive blast or use water jetting, SP 11 is recommended. It is considered equivalent to SP 6. SP 11 is also preferred wherever SP 2 or SP 3 are shown in the Table.

^b These are minimum requirements. A high-performing system may be a better choice for longer performance.

^c For marine, chemical, or immersion service, or application of heat resistant or nonslip floor coatings. SP 10 is preferred for zinc-rich primers, and for extremely severe environments where long-term performance is desired.

^d Use water jetting to SP 12 WJ-3, as alternate to SP 6 degree of cleanliness.

^e Use only the steam clean, or non-alkaline detergent solutions of SP 1.

^f First, remove chalk and dirt with a non-alkaline detergent solution, and follow with power wash at minimum 2000 psi. Second, spot clean, in order of preference by SP 6, SP 11, SP 7, SP 3, or SP 2.

^g First, remove chalk and dirt with a non-alkaline detergent solution, and follow with power wash at minimum 2000 psi. Second, spot clean, in order of preference, by SP 10, SP 6, or SP 11.

^h **SSPC SP 12/NACE No.5** provides four levels of water jetting cleanliness and they reflect the four levels of abrasive blast cleanliness but direct correlation is inaccurate or inappropriate. The four levels are (best to worst): WJ-1, WJ-2, WJ-3, and WJ-4. They are equivalent to the abrasive blast standards SSPC SP 5, SP 10, SP 6, and SP 7. The standard also includes three levels of cleanliness for nonvisual contaminants, SC-1, SC-2, and SC-3. The preferred level of cleanliness is between SC-1 or SC-2.

a. Ferrous Surfaces including Shop-coated Surfaces and Small Areas That Contain Rust, Mill Scale and Other Foreign Substances: [Solvent clean] [or] [detergent wash] in accordance with **SSPC SP 1** to remove oil and grease. Where shop coat is missing or damaged, clean according to [**SSPC SP 2,**] [**SSPC SP 3,**] [**SSPC SP 6/NACE No.3,**] or [**SSPC SP 10/NACE No. 2.**]. [Brush-off blast remaining surface in accordance with **SSPC 7/NACE No.4**]; [Water jetting to **SSPC SP 12/NACE No.5** WJ-4 may be used to remove loose coating and other loose materials. Use inhibitor as recommended by coating manufacturer to prevent premature rusting.] Protect shop-coated ferrous surfaces from corrosion by treating and touching up corroded areas immediately upon detection.

b. Surfaces With More Than 20 Percent Rust, Mill Scale, and Other Foreign Substances: Clean entire surface in accordance with [**SSPC SP 6/NACE**

No.3/SSPC SP 12/NACE No.5 WJ-3][SSPC SP 10/NACE No. 2/SSPC SP 12/NACE No.5 WJ-2].

[c. Metal Floor Surfaces to Receive Nonslip Coating: Clean in accordance with [SSPC SP 10/NACE No. 2][SSPC SP 12/NACE No.5 WJ-2].

]3.5.2 Final Ferrous Surface Condition:

Type Coating	Level of Cleaning, SSPC SP ...
a. Latex or Alkyd	2,3,6 or SP 12 WJ-2.(7 and 10, SP 12 WJ-2 or SP 12 WJ-1 may be left in as Contractor options)
b. High Performance (i.e. Epoxy, Urethane, others)	7,10

For tool cleaned surfaces, the requirements are stated in [SSPC SP 2](#) and [SSPC SP 3](#). Use as a visual reference, photographs in [SSPC VIS 3](#) for the appearance of cleaned surfaces.

For abrasive blast cleaned surfaces, the requirements are stated in [SSPC 7/NACE No.4](#), [SSPC SP 6/NACE No.3](#), and [SSPC SP 10/NACE No. 2](#). Use as a visual reference, photographs in [SSPC VIS 1](#) for the appearance of cleaned surfaces.

For waterjet cleaned surfaces, the requirements are stated in [SSPC SP 12/NACE No.5](#). Use as a visual reference, photographs in [SSPC VIS 4/NACE VIS 7](#) for the appearance of cleaned surfaces.

3.5.3 Galvanized Surfaces

- a. New or Existing Galvanized Surfaces With Only Dirt and Zinc Oxidation Products: Clean with [solvent,][steam,][or][non-alkaline detergent solution]in accordance with [SSPC SP 1](#). Completely remove coating by brush-off abrasive blast if the galvanized metal has been passivated or stabilized. Do not "passivate" or "stabilize" new galvanized steel to be coated. If the absence of hexavalent stain inhibitors is not documented, test as described in [ASTM D6386](#), Appendix X2, and remove by one of the methods described therein.
- b. Galvanized with Slight Coating Deterioration or with Little or No Rusting: Water jetting to [SSPC SP 12/NACE No.5 WJ3](#) to remove loose coating from surfaces with less than 20 percent coating deterioration and no blistering, peeling, or cracking. Use inhibitor as recommended by the coating manufacturer to prevent rusting.
- c. Galvanized With Severe Deteriorated Coating or Severe Rusting: [Water jet to [SSPC SP 12/NACE No.5 WJ3](#) degree of cleanliness.] [Spot abrasive blast rusted areas as described for steel in [SSPC SP 6/NACE No.3](#), and waterjet to [SSPC SP 12/NACE No.5](#), WJ3 to remove existing coating.]

3.5.4 Non-Ferrous Metallic Surfaces

Aluminum and aluminum-alloy, lead, copper, and other nonferrous metal surfaces.

Surface Cleaning: Solvent clean in accordance with **SSPC SP 1** and wash with mild non-alkaline detergent to remove dirt and water soluble contaminants.

3.5.5 Terne-Coated Metal Surfaces

Solvent clean surfaces with mineral spirits, **ASTM D235**. Wipe dry with clean, dry cloths.

3.5.6 Existing Surfaces with a Bituminous or Mastic-Type Coating

Remove chalk, mildew, and other loose material by washing with a solution of **0.20 liter (1/2 cup)** trisodium phosphate, **0.1 liter (1/4 cup)** household detergent, **1.6 liters (one quart)** 5 percent sodium hypochlorite solution and **4.8 liters (3 quarts)** of warm water.

3.6 PREPARATION OF CONCRETE AND CEMENTITIOUS SURFACE

3.6.1 Concrete and Masonry

a. Curing: Allow concrete, stucco and masonry surfaces to cure at least 30 days before painting, and concrete slab on grade to cure at least 90 days before painting.

b. Surface Cleaning: Remove the following deleterious substances.

(1) Dirt, [Chalking,] Grease, and Oil: Wash new[and existing uncoated] surfaces with a solution composed of **0.2 liter (1/2 cup)** trisodium phosphate, **0.1 liter (1/4 cup)** household detergent, and **6.4 liters (4 quarts)** of warm water. Then rinse thoroughly with fresh water.[Wash existing coated surfaces with a suitable detergent and rinse thoroughly.] For large areas, water blasting may be used.

(2) Fungus and Mold: Wash [new][, existing coated,] [and existing uncoated] surfaces with a solution composed of **0.2 liter (1/2 cup)** trisodium phosphate, **0.1 liter (1/4 cup)** household detergent, **1.6 liters (1 quart)** 5 percent sodium hypochlorite solution and **4.8 liters (3 quarts)** of warm water. Rinse thoroughly with fresh water.

(3) Paint and Loose Particles: Remove by wire brushing.

(4) Efflorescence: Remove by scraping or wire brushing followed by washing with a 5 to 10 percent by weight aqueous solution of hydrochloric (muriatic) acid. Do not allow acid to remain on the surface for more than five minutes before rinsing with fresh water. Do not acid clean more than **0.4 square meter (4 square feet)** of surface, per workman, at one time.

[(5) Removal of Existing Coatings: For surfaces to receive textured coating **MPI 42**, remove existing coatings including soundly adhered coatings if recommended by textured coating manufacturer.

-]c. Cosmetic Repair of Minor Defects: Repair or fill mortar joints and minor defects, including but not limited to spalls, in accordance with manufacturer's recommendations and prior to coating application.
- d. Allowable Moisture Content: Latex coatings may be applied to damp surfaces, but not to surfaces with droplets of water. Do not apply epoxies to damp vertical surfaces as determined by ASTM D4263 or horizontal surfaces that exceed 3 lbs of moisture per 1000 square feet in 24 hours as determined by ASTM F1869. In all cases follow manufacturers recommendations. Allow surfaces to cure a minimum of 30 days before painting.

3.6.2 Gypsum Board, Plaster, and Stucco

- a. Surface Cleaning: Verify that plaster and stucco surfaces are free from loose matter and that gypsum board is dry. Remove loose dirt and dust by brushing with a soft brush, rubbing with a dry cloth, or vacuum-cleaning prior to application of the first coat material. A damp cloth or sponge may be used if paint will be water-based.
- b. Repair of Minor Defects: Prior to painting, repair joints, cracks, holes, surface irregularities, and other minor defects with patching plaster or spackling compound and sand smooth.
- c. Allowable Moisture Content: Latex coatings may be applied to damp surfaces, but not surfaces with droplets of water. Do not apply epoxies to damp surfaces as determined by ASTM D4263. Verify that new plaster to be coated has a maximum moisture content of 8 percent, when measured in accordance with ASTM D4444, Method A, unless otherwise authorized. In addition to moisture content requirements, allow new plaster to age a minimum of 30 days before preparation for painting.

3.6.3 Existing Asbestos Cement Surfaces

Remove oily stains by solvent cleaning with mineral spirits, [MIL-PRF-680][ASTM D235]. Remove loose dirt, dust, and other deleterious substances by brushing with a soft brush or rubbing with a dry cloth prior to application of the first coat material. Do not wire brush or clean using other abrasive methods. Verify surfaces are dry and clean prior to application of the coating.

3.7 PREPARATION OF WOOD AND PLYWOOD SURFACES

3.7.1 New [, Existing Uncoated,] [and] [Existing Coated] Plywood and Wood Surfaces, Except Floors:

- a. Clean wood surfaces of foreign matter.

Surface Cleaning: Verify that surfaces are free from dust and other deleterious substances and in a condition approved by the Contracting Officer prior to receiving paint or other finish. Do not use water to clean uncoated wood.[Scrape to remove loose coatings. Lightly sand to roughen the entire area of previously enamel-coated wood surfaces.]

- [b. Removal of Fungus and Mold: Wash existing coated surfaces with a solution composed of 0.2 liter (3 ounces (2/3 cup)) trisodium

phosphate, 0.1 liter (1 ounce (1/3 cup)) household detergent, 1.6 liters (1 quart) 5 percent sodium hypochlorite solution and 4.8 liters (3 quarts) of warm water. Rinse thoroughly with fresh water.

-].c. Do not exceed 12 percent moisture content of the wood as measured by a moisture meter in accordance with ASTM D4444, Method A, unless otherwise authorized.
- d. Prime or touch up wood surfaces adjacent to surfaces to receive water-thinned paints before applying water-thinned paints.
- e. Cracks and Nailheads: Set and putty stop nailheads and putty cracks after the prime coat has dried.
- f. Cosmetic Repair of Minor Defects:
 - (1) Knots and Resinous Wood [and Fire, Smoke, Water, and Color Marker Stained Existing Coated Surface]: Prior to application of coating, cover knots and stains with two or more coats of 1.3-kg-cut (3-pound-cut) shellac varnish, plasticized with 0.14 liters (5 ounces) of castor oil per liter (gallon). Scrape away existing coatings from knotty areas, and sand before treating. Prime before applying any putty over shellacked area.
 - (2) Open Joints and Other Openings: Fill with whiting putty, linseed oil putty. Sand smooth after putty has dried.
 - (3) Checking: Where checking of the wood is present, sand the surface, wipe and apply a coat of pigmented orange shellac. Allow to dry before paint is applied.
- g. Prime Coat For New Exterior Surfaces: Prime coat [wood doors,] [windows,] [frames,] [and] [trim] before wood becomes dirty, warped, [or weathered].

3.7.2 Wood Floor Surfaces, Natural Finish

- a. Initial Surface Cleaning: As specified in paragraph entitled "Surface Preparation."
-].b. Existing Loose Boards and Shoe Molding: Before sanding, renail loose boards. Countersink nails and fill with an approved wood filler. Remove shoe molding before sanding and reinstall after completing other work. At Contractor's option, new shoe molding may be provided in lieu of reinstalling old. Provide new wood molding of the same size, wood species, and finish as the existing.
-].c. Sanding and Scraping: Sanding of wood floors is specified in Section [09 64 29 WOOD STRIP AND PLANK FLOORING] [09 64 23 WOOD PARQUET FLOORING] [09 64 66 WOOD ATHLETIC FLOORING] [09 64 00 PORTABLE (DEMOUNTABLE) WOOD FLOORING]. Fill floors of oak or similar open-grain wood with wood filler recommended by the finish manufacturer and the excess filler removed.
- d. Final Cleaning: After sanding, sweep and vacuum floors clean. Do not walk on floors thereafter until specified sealer has been applied and is dry.

3.7.3 Interior Wood Surfaces, Stain Finish

Sand interior wood surfaces to receive stain. Fill oak and other open-grain wood to receive stain with a coat of wood filler not less than 8 hours before the application of stain; remove excess filler and sand the surface smooth.

3.7.4 Water Blasting of Existing Coated Wood Surfaces:

Provide water blasting for the following surfaces: [_____].

- a. Sample Panel: Prior to the initial surface cleaning, water blast a representative surface designated by the Contracting Officer. Provide surface cleaning of the remaining work to match the sample panel approved by the Contracting Officer.
- b. Initial Surface Cleaning: Water blast surfaces to receive paint with a high pressure spray, to remove loose paint, dirt, and other foreign or deleterious materials. Provide working pressure between 2.8 and 4.8 MPa (400 and 700 pounds per square inch gage (psig)) at a nozzle operating rate of a minimum 75 liters per minute (l/min) (20 gallons per minute (g/min.)). Do not flood vents or damage windows and floors. If the pressure specified will cause damage to existing wood, advise the Contracting Officer and obtain permission to vary the pressure. Direct the wash nozzle at the surface at an angle of approximately 75 degrees with the surface and at a distance not greater than 1500 mm (5 feet) to apply water pressure required to remove loose paint, dirt, chalking, and other foreign matter.
- c. Final Surface Cleaning: After allowing the surfaces to dry for a minimum of 24 hours, remove remaining dirt, splinters, loose particles, disintegrated and loose paint, grease, oil, and other foreign matter from the surface.

3.8 APPLICATION

3.8.1 Coating Application

Comply with applicable federal, state and local laws enacted to insure compliance with Federal Clean Air Standards. Apply coating materials in accordance with SSPC PA 1. SSPC PA 1 methods are applicable to all substrates, except as modified herein.

At the time of application, paint must show no signs of deterioration. Maintain uniform suspension of pigments during application.

Unless otherwise specified or recommended by the paint manufacturer, paint may be applied by brush, roller, or spray. Use trigger operated spray nozzles for water hoses. Use rollers for applying paints and enamels of a type designed for the coating to be applied and the surface to be coated. Wear protective clothing and respirators when applying oil-based paints or using spray equipment with any paints.

Only apply paints, except water-thinned types to surfaces that are completely free of moisture as determined by sight or touch.

Thoroughly work coating materials into joints, crevices, and open spaces. Pay special attention to ensure that all edges, corners, crevices, welds, and rivets receive a film thickness equal to that of adjacent painted surfaces.

Apply each coat of paint so that dry film is of uniform thickness and free from runs, drops, ridges, waves, pinholes or other voids, laps, brush marks, and variations in color, texture, and finish. Completely hide all blemishes.

Touch up damaged coatings before applying subsequent coats. [Broom clean and clear dust from interior areas before and during the application of coating material.]

[Apply paint to new fire extinguishing sprinkler systems including valves, piping, conduit, hangers, supports, miscellaneous metal work, and accessories. Shield sprinkler heads with protective coverings while painting is in progress. Remove sprinkler heads which have been painted and replace with new sprinkler heads. For piping in unfinished spaces, provide primed surfaces with one coat of red alkyd gloss enamel to a minimum dry film thickness of 0.025 mm (1.0 mil). Unfinished spaces include attic spaces, spaces above suspended ceilings, crawl spaces, pipe chases, mechanical equipment room, and space where walls or ceiling are not painted or not constructed of a prefinished material. For piping in finished areas, provide prime surfaces with two coats of paint to match adjacent surfaces, except provide valves and operating accessories with one coat of red alkyd gloss enamel. Upon completion of painting, remove protective covering from sprinkler heads.

- ja. Drying Time: Allow time between coats, as recommended by the coating manufacturer, to permit thorough drying, but not to present topcoat adhesion problems. Provide each coat in specified condition to receive next coat.
- b. Primers, and Intermediate Coats: Do not allow primers or intermediate coats to dry more than 30 days, or longer than recommended by manufacturer, before applying subsequent coats. Follow manufacturer's recommendations for surface preparation if primers or intermediate coats are allowed to dry longer than recommended by manufacturers of subsequent coatings. Cover each preceding coat or surface completely by ensuring visually perceptible difference in shades of successive coats.
- c. Finished Surfaces: Provide finished surfaces free from runs, drops, ridges, waves, laps, brush marks, and variations in colors.
- d. Thermosetting Paints: Topcoats over thermosetting paints (epoxies and urethanes) should be applied within the overcoating window recommended by the manufacturer.
- e. Floors: [For nonslip surfacing on level floors, as the intermediate coat is applied, cover wet surface completely with almandite garnet, Grit No. 36, with maximum passing U.S. Standard Sieve No. 40 less than 0.5 percent. When the coating is dry, use a soft bristle broom to sweep up excess grit, which may be reused, and vacuum up remaining residue before application of the topcoat.] [For nonslip surfacing on

ramps, provide MPI 77 with non-skid additive, applied by roller in accordance with manufacturer's instructions.]

3.8.2 Mixing and Thinning of Paints

Reduce paints to proper consistency by adding fresh paint, except when thinning is mandatory to suit surface, temperature, weather conditions, application methods, or for the type of paint being used. Obtain written permission from the Contracting Officer to use thinners. Verify that the written permission includes quantities and types of thinners to use.

When thinning is allowed, thin paints immediately prior to application with not more than [0.125 L] [1 pint] of suitable thinner per [liter.] [gallon.] The use of thinner does not relieve the Contractor from obtaining complete hiding, full film thickness, or required gloss. Thinning cannot cause the paint to exceed limits on volatile organic compounds. Do not mix paints of different manufacturers.

3.8.3 Two-Component Systems

Mix two-component systems in accordance with manufacturer's instructions. Follow recommendation by the manufacturer for any thinning of the first coat to ensure proper penetration and sealing for each type of substrate.

3.8.4 Coating Systems

- a. Systems by Substrates: Apply coatings that conform to the respective specifications listed in the following Tables:

Table

Division 3.	Exterior Concrete Paint Table
Division 4.	Exterior Concrete Masonry Units Paint Table
Division 5.	Exterior Metal, Ferrous and Non-Ferrous Paint Table
Division 6.	Exterior Wood; Dressed Lumber, Paneling, Decking, Shingles Paint Table
Division 9:	Exterior Stucco Paint Table
Division 10.	Exterior Cloth Coverings and Bituminous Coated Surfaces Paint Table
Division 3.	Interior Concrete Paint Table
Division 4.	Interior Concrete Masonry Units Paint Table
Division 5.	Interior Metal, Ferrous and Non-Ferrous Paint Table
Division 6.	Interior Wood Paint Table
Division 9:	Interior Plaster, Gypsum Board, Textured Surfaces Paint Table

- b. Minimum Dry Film Thickness (DFT): Apply paints, primers, varnishes, enamels, undercoats, and other coatings to a minimum dry film thickness of 0.038 mm (1.5 mil) each coat unless specified otherwise in the Tables. Coating thickness where specified, refers to the minimum dry film thickness.
- c. Coatings for Surfaces Not Specified Otherwise: Coat surfaces which have not been specified, the same as surfaces having similar conditions of exposure.

- d. Existing Surfaces Damaged During Performance of the Work, Including New Patches In Existing Surfaces: Coat surfaces with the following:
 - (1) One coat of primer.
 - (2) One coat of undercoat or intermediate coat.
 - (3) One topcoat to match adjacent surfaces.
- e. Existing Coated Surfaces To Be Painted: Apply coatings conforming to the respective specifications listed in the Tables herein, except that pretreatments, sealers and fillers need not be provided on surfaces where existing coatings are soundly adhered and in good condition. Do not omit undercoats or primers.

3.9 COATING SYSTEMS FOR METAL

Apply coatings of Tables in Division 5 for Exterior and Interior.

- a. Apply specified ferrous metal primer on the same day that surface is cleaned, to surfaces that meet all specified surface preparation requirements at time of application.
- b. Inaccessible Surfaces: Prior to erection, use one coat of specified primer on metal surfaces that will be inaccessible after erection.
- c. Shop-primed Surfaces: Touch up exposed substrates and damaged coatings to protect from rusting prior to applying field primer.
- d. Surface Previously Coated with Epoxy or Urethane: Apply MPI 101, 0.038 mm (1.5 mils) DFT immediately prior to application of epoxy or urethane coatings.
- e. Pipes and Tubing: The semitransparent film applied to some pipes and tubing at the mill is not to be considered a shop coat. Overcoat these items with the specified ferrous-metal primer prior to application of finish coats.
- f. Exposed Nails, Screws, Fasteners, and Miscellaneous Ferrous Surfaces. On surfaces to be coated with water thinned coatings, spot prime exposed nails and other ferrous metal with latex primer MPI 107.

3.10 COATING SYSTEMS FOR CONCRETE AND CEMENTITIOUS SUBSTRATES

Apply coatings of Tables in Division 3, 4 and 9 for Exterior and Interior.

3.11 COATING SYSTEMS FOR WOOD AND PLYWOOD

- a. Apply coatings of Tables in Division 6 for Exterior and Interior.
- b. Prior to erection, apply two coats of specified primer to treat and prime wood [and plywood] surfaces which will be inaccessible after erection.
- c. Apply stains in accordance with manufacturer's printed instructions.

[d. Wood Floors to Receive Natural Finish: Thin first coat 2 to 1 using thinner recommended by coating manufacturer. Apply all coatings at rate of 30 square meters per 4 liters (300 to 350 square feet per gallon). Apply second coat not less than 2 hours and not over 24 hours after first coat has been applied. Apply with lambs wool applicators or roller as recommended by coating manufacturer. Buff or lightly sand between intermediate coats as recommended by coating manufacturer's printed instructions.

]3.12 PIPING IDENTIFICATION

Piping Identification, Including Surfaces In Concealed Spaces: Provide in accordance with [MIL-STD-101][ASME A13.1]. Place stenciling in clearly visible locations. On piping not covered by [MIL-STD-101][ASME A13.1], stencil approved names or code letters, in letters a minimum of 13 mm (1/2 inch) high for piping and a minimum of 50 mm (2 inches) high elsewhere. Stencil arrow-shaped markings on piping to indicate direction of flow using black stencil paint.

3.13 INSPECTION AND ACCEPTANCE

In addition to meeting previously specified requirements, demonstrate mobility of moving components, including swinging and sliding doors, cabinets, and windows with operable sash, for inspection by the Contracting Officer. Perform this demonstration after appropriate curing and drying times of coatings have elapsed and prior to invoicing for final payment.

3.14 WASTE MANAGEMENT

As specified in the Waste Management Plan and as follows. Do not use kerosene or any such organic solvents to clean up water based paints. Properly dispose of paints or solvents in designated containers. Close and seal partially used containers of paint to maintain quality as necessary for reuse. Store in protected, well-ventilated, fire-safe area at moderate temperature. Place materials defined as hazardous or toxic waste in designated containers.[Coordinate with manufacturer for take-back program. Set aside scrap to be returned to manufacturer for recycling into new product. When such a service is not available, contact local recyclers to reclaim the materials.][Set aside extra paint for future color matches or reuse by the Government.][Where local options exist for leftover paint recycling, collect all waste paint by type and provide for delivery to recycling or collection facility for reuse by local organizations.]

3.15 PAINT TABLES

All DFT's are minimum values.[Use only materials with a GPS green check mark having a minimum MPI "Environmentally Friendly" [E1] [E2] [E3] rating based on VOC (EPA Method 24) content levels.] Acceptable products are listed in the MPI Green Approved Products List, available at <http://www.specifygreen.com/APL/ProductIdxByMPInum.asp>.

Gloss Level	Description	Units at 60 degrees	Units at 85 degrees
G1	Matte or Flat	0 to 5	10 max
G2	Velvet	0 to 10	10 to 35
G3	Eggshell	10 to 25	10 to 35
G4	Satin	20 to 35	35 min

G5	Semi-Gloss	35 to 70
G6	Gloss	70 to 85
G7	High Gloss	

3.15.1 Exterior Paint Tables

DIVISION 3: EXTERIOR CONCRETE PAINT TABLE

A. [New and uncoated existing] [and Existing, previously painted] concrete; vertical surfaces, including undersides of balconies and soffits but excluding tops of slabs:

1. [Latex

[New; MPI EXT 3.1A-G2 (Flat) / Existing; MPI REX 3.1A-G2 (Flat)

Primer:	Intermediate:	Topcoat:
MPI 10	MPI 10	MPI 10

System DFT: 88 microns (3.5 mils)]

[New; MPI EXT 3.1A-G5 (Semigloss) / Existing; MPI EXT 3.1A-G5 (Semigloss)

Primer:	Intermediate:	Topcoat:
MPI 11	MPI 11	MPI 11

System DFT: 88 microns (3.5 mils)]

[New; MPI EXT 3.1A-G6 (Gloss) / Existing; MPI REX 3.1A-G6 (Gloss)

Primer:	Intermediate:	Topcoat:
MPI 119	MPI 119	MPI 119

System DFT: 88 microns (3.5 mils)]

Primer as recommended by manufacturer. Topcoat: Coating to match adjacent surfaces.]

B. [New and uncoated existing] [and Existing, previously painted] concrete, textured system; vertical surfaces, including undersides of balconies and soffits but excluding tops of slabs:

1. [Latex Aggregate

[New; MPI EXT 3.1B-G2 (Flat) / Existing; MPI REX 3.1B-G2 (Flat)

Primer:	Intermediate:	Topcoat:
MPI 42	MPI 10	MPI 10

System DFT: Per Manufacturer]

[New; MPI EXT 3.1B-G5 (Semigloss) / Existing; MPI REX 3.1B-G5 (Semigloss)

Primer:	Intermediate:	Topcoat:
MPI 42	MPI 11	MPI 11

System DFT: Per Manufacturer]

[New; MPI EXT 3.1B-G6 (Gloss) / Existing; MPI REX 3.1B-G6 (Gloss)

Primer:	Intermediate:	Topcoat:
MPI 42	MPI 119	MPI 119

System DFT: Per Manufacturer]

Texture - [Fine] [Medium] [Coarse]. Surface preparation and number of coats in accordance with manufacturer's instructions. Topcoat: Coating to match adjacent surfaces.]

C. [New and uncoated existing] [and Existing, previously painted] concrete, elastomeric System; vertical surfaces, including undersides of balconies

and soffits but excluding tops of slabs:

1. [Elastomeric Coating

New; MPI EXT 3.1F / Existing; MPI REX 3.1F

Primer: Intermediate: Topcoat:

Per Manufacturer MPI 113 MPI 113

System DFT: 400 microns (16 mils)

Primer as recommended by manufacturer. Topcoat: Coating to match adjacent surfaces. Surface preparation and number of coats in accordance with manufacturer's instructions.

NOTE: Apply sufficient coats of MPI 113 to achieve a minimum dry film thickness of 400 microns (16 mils).]

D. [New and uncoated existing] [and Existing, previously painted] concrete: walls and bottom of swimming pools.

1. [Chlorinated Rubber

New; / Existing;

Primer: Intermediate: Topcoat:

SSPC Paint 18 SSPC Paint 18 SSPC Paint 18

System DFT: Per Manufacturer

NOTE: Thin first coat (primer) with 1 part of approved thinner to 4 parts of paint by volume.]

E. [New] [and Existing] Cementitious composition board (including Asbestos cement board):

1. [Latex

[New; MPI EXT 3.3A-G1 (Flat) /Existing; MPI REX 3.3A-G1 (Flat)

Primer: Intermediate: Topcoat:

MPI 10 MPI 10 MPI 10

System DFT: 112 microns (4.5 mils)]

[New; MPI EXT 3.3A-G5 (Semigloss) / Existing; MPI REX 3.3A-G5 (Semigloss)

Primer: Intermediate: Topcoat:

MPI 11 MPI 11 MPI 11

System DFT: 112 microns (4.5 mils)]

[New; MPI EXT 3.3A-G6 (Gloss) / Existing; MPI REX 3.3A-G6 (Gloss)

Primer: Intermediate: Topcoat:

MPI 119 MPI 119 MPI 119

System DFT: 112 microns (4.5 mils)]

Topcoat: Coating to match adjacent surfaces.]

DIVISION 4: EXTERIOR CONCRETE MASONRY UNITS PAINT TABLE

A. [New] [and Existing] concrete masonry on uncoated surface:

1. [Latex

[New; MPI EXT 4.2A-G1 (Flat) / Existing; MPI REX 4.2A-G1 (Flat)

Block Filler: Primer: Intermediate: Topcoat:

STEEL / FERROUS SURFACES

A. New Steel that has been hand or power tool cleaned to **SSPC SP 2** or **SSPC SP 3**

1. [Alkyd
[New; MPI EXT 5.1Q-G5 (Semigloss) Existing; MPI REX 5.1D-G5
Primer: Intermediate: Topcoat:
MPI 23 MPI 94 MPI 94
System DFT: 131 microns (5.25 mils)]

[New; MPI EXT 5.1Q-G6 (Gloss) / Existing; MPI REX 5.1D-G6
Primer: Intermediate: Topcoat:
MPI 23 MPI 9 MPI 9
System DFT: 131 microns (5.25 mils)]]

B. New Steel that has been blast-cleaned to **SSPC SP 6/NACE No.3**:

2. [Alkyd
[New; MPI EXT 5.1D-G5 (Semigloss) / Existing; MPI REX 5.1D-G5
Primer: Intermediate: Topcoat:
MPI 79 MPI 94 MPI 94
System DFT: 131 microns (5.25 mils)]

[New; MPI EXT 5.1D-G6 (Gloss) / Existing; MPI REX 5.1D-G6
Primer: Intermediate: Topcoat:
MPI 79 MPI 9 MPI 9
System DFT: 131 microns (5.25 mils)]]

C. Existing steel that has been spot-blasted to **SSPC SP 6/NACE No.3**:

1. [Surface previously coated with alkyd or latex:

[Waterborne Light Industrial Coating
MPI REX 5.1C-G5 (Semigloss)
Spot Primer: Intermediate: Topcoat:
MPI 79 MPI 163 MPI 163
System DFT: 125 microns (5 mils)]

[MPI REX 5.1C-G6 (Gloss)
Spot Primer: Intermediate: Topcoat:
MPI 79 MPI 164 MPI 164
System DFT: 125 microns (5 mils)]]
2. [Surface previously coated with epoxy:

[Waterborne Light Industrial
a. MPI REX 5.1L-G5 (Semigloss)
Spot Primer: Intermediate: Topcoat:
MPI 101 MPI 163 MPI 163
System DFT: 125 microns (5 mils)]

[MPI REX 5.1L-G6 (Gloss)
Spot Primer: Intermediate: Topcoat:
MPI 101 MPI 164 MPI 164
System DFT: 125 microns (5 mils)]

[Pigmented Polyurethane
b. MPI REX 5.1H-G6 (Gloss)
Spot Primer: Intermediate: Topcoat:
MPI 101 MPI 108 MPI 72
System DFT: 212 microns (8.5 mils)]]

D. New [and existing] steel blast cleaned to SSPC SP 10/NACE No. 2:

1. [Waterborne Light Industrial
[MPI EXT 5.1R-G5 (Semigloss)
Primer: Intermediate: Topcoat:
MPI 101 MPI 108 MPI 163
System DFT: 212 microns (8.5 mils)]

[MPI EXT 5.1R-G6 (Gloss)
Primer: Intermediate: Topcoat:
MPI 101 MPI 108 MPI 164
System DFT: 212 microns (8.5 mils)]]

2. [Pigmented Polyurethane
MPI EXT 5.1J-G6 (Gloss)
Primer: Intermediate: Topcoat:
MPI 101 MPI 108 MPI 72
System DFT: 212 microns (8.5 mils)]

E. Metal floors (non-shop-primed surfaces or non-slip deck surfaces) with non-skid additive (NSA), load at manufacturer's recommendations.:

1. [Alkyd Floor Enamel
MPI EXT 5.1S-G6 (Gloss)
Primer: Intermediate: Topcoat:
MPI 79 MPI 27 MPI 27 (plus NSA)
System DFT: 131 microns (5.25 mils)]

EXTERIOR GALVANIZED SURFACES

F. New Galvanized surfaces:

1. [Cementitious primer / Latex
[MPI EXT 5.3A-G1 (Flat)
Primer: Intermediate: Topcoat:
MPI 26 MPI 10 MPI 10
System DFT: 112 microns (4.5 mils)]

[MPI EXT 5.3A-G5 (Semigloss)
Primer: Intermediate: Topcoat:
MPI 26 MPI 11 MPI 11
System DFT: 112 microns (4.5 mils)]

[MPI EXT 5.3A-G6 (Gloss)
Primer: Intermediate: Topcoat:
MPI 26 MPI 119 MPI 119
System DFT: 112 microns (4.5 mils)]]

2. [Waterborne Primer / Latex
[MPI EXT 5.3H-G1 (Flat)
Primer: Intermediate: Topcoat:

- MPI 134 MPI 10 MPI 10
System DFT: 112 microns (4.5 mils)]
- [MPI EXT 5.3H-G5 (Semigloss)
Primer: Intermediate: Topcoat:
MPI 134 MPI 11 MPI 11
System DFT: 112 microns (4.5 mils)]
- [MPI EXT 5.3H-G6 (Gloss)
Primer: Intermediate: Topcoat:
MPI 134 MPI 119 MPI 119
System DFT: 112 microns (4.5 mils)]]
3. [Waterborne Primer / Waterborne Light Industrial Coating
[MPI EXT 5.3J-G5 (Semigloss)
Primer: Intermediate: Topcoat:
MPI 134 MPI 163 MPI 163
System DFT: 112 microns (4.5 mils)]
- [MPI EXT 5.3J-G6 (Gloss)
Primer: Intermediate: Topcoat:
MPI 134 MPI 164 MPI 164
System DFT: 112 microns (4.5 mils)]]
4. [Epoxy Primer / Waterborne Light Industrial Coating
[MPI EXT 5.3K-G5 (Semigloss)
Primer: Intermediate: Topcoat:
MPI 101 MPI 163 MPI 163
System DFT: 125 microns (5 mils)]
- [MPI EXT 5.3K-G6 (Gloss)
Primer: Intermediate: Topcoat:
MPI 101 MPI 164 MPI 164
System DFT: 125 microns (5 mils)]]
5. [Pigmented Polyurethane
MPI EXT 5.3L-G6 (Gloss)
Primer: Intermediate: Topcoat:
MPI 101 N/A MPI 72
System DFT: 125 microns (5 mils)]
- G. Galvanized surfaces with slight coating deterioration; little or no rusting:
1. [Waterborne Light Industrial Coating
MPI REX 5.3J-G5 (Semigloss)
Primer: Intermediate: Topcoat:
MPI 134 N/A MPI 163
System DFT: 112 microns (4.5 mils)]
2. [Pigmented Polyurethane
MPI REX 5.3D-G6 (Gloss)
Primer: Intermediate: Topcoat:
MPI 101 N/A MPI 72
System DFT: 125 microns (5 mils)]
- H. Galvanized surfaces with severely deteriorated coating or rusting:

1. [Waterborne Light Industrial Coating
 [MPI REX 5.3L-G5 (Semigloss)
 Primer: Intermediate: Topcoat:
 MPI 101 MPI 108 MPI 163
 System DFT: 212 microns (8.5 mils)]

 [MPI REX 5.3L-G6 (Gloss)
 Primer: Intermediate: Topcoat:
 MPI 101 MPI 108 MPI 164
 System DFT: 212 microns (8.5 mils)]]
2. [Pigmented Polyurethane
 MPI REX 5.3K-G6 (Gloss)
 Primer: Intermediate: Topcoat:
 MPI 101 MPI 108 MPI 72
 System DFT: 125 microns (5 mils)]

EXTERIOR SURFACES, OTHER METALS (NON-FERROUS)

I. Aluminum, aluminum alloy and other miscellaneous non-ferrous metal items not otherwise specified except hot metal surfaces, roof surfaces, and new prefinished equipment. Match surrounding finish:

1. [Alkyd
 [MPI EXT 5.4F-G1 (Flat)
 Primer: Intermediate: Topcoat:
 MPI 95 MPI 8 MPI 8
 System DFT: 125 microns (5 mils)]

 [MPI EXT 5.4F-G5 (Semigloss)
 Primer: Intermediate: Topcoat:
 MPI 95 MPI 94 MPI 94
 System DFT: 125 microns (5 mils)]

 [MPI EXT 5.4F-G6 (Gloss)
 Primer: Intermediate: Topcoat:
 MPI 95 MPI 9 MPI 9
 System DFT: 125 microns (5 mils)]]
2. [Waterborne Light Industrial Coating
 [MPI EXT 5.4G-G3 (Eggshell)
 Primer: Intermediate: Topcoat:
 MPI 95 MPI 161 MPI 161
 System DFT: 125 microns (5 mils)]

 [MPI EXT 5.4G-G5 (Semigloss)
 Primer: Intermediate: Topcoat:
 MPI 95 MPI 163 MPI 163
 System DFT: 125 microns (5 mils)]

 [MPI EXT 5.4G-G6 (Gloss)
 Primer: Intermediate: Topcoat:
 MPI 95 MPI 164 MPI 164
 System DFT: 125 microns (5 mils)]]

I. Existing roof surfaces previously coated:

1. [Aluminum Pigmented Asphalt Roof Coating
ASTM D2824/D2824M: Sufficient coats to provide not less than 200 microns
(8 mils)
of finished coating system (without asbestos fibers).]

2. [Aluminum Paint
MPI REX 10.2D
Primer: Intermediate: Topcoat:
MPI 107 MPI 1 MPI 1
System DFT: 88 microns (3.5 mils)]

J. Surfaces adjacent to painted surfaces; [Mechanical,] [Electrical,] [Fire
extinguishing sprinkler systems including valves, conduit, hangers,
supports,][exposed copper piping,] [and miscellaneous metal items] not
otherwise specified except floors, hot metal surfaces, and new prefinished
equipment. Match surrounding finish:

1. [Alkyd
[MPI EXT 5.1D-G1 (Flat)
Primer: Intermediate: Topcoat:
MPI 79 MPI 8 MPI 8
System DFT: 131 microns (5.25 mils)]

[MPI EXT 5.1D-G5 (Semigloss)
Primer: Intermediate: Topcoat:
MPI 79 MPI 94 MPI 94
System DFT: 131 microns (5.25 mils)]

[MPI EXT 5.1D-G6 (Gloss)
Primer: Intermediate: Topcoat:
MPI 79 MPI 9 MPI 9
System DFT: 131 microns (5.25 mils)]]

2. [Waterborne Light Industrial Coating
[MPI EXT 5.1C-G3(Eggshell)
Primer: Intermediate: Topcoat:
MPI 79 MPI 161 MPI 161
System DFT: 125 microns (5 mils)]

[MPI EXT 5.1C-G5(Semigloss)
Primer: Intermediate: Topcoat:
MPI 79 MPI 163 MPI 163
System DFT: 125 microns (5 mils)]

[MPI EXT 5.1C-G6(Gloss)
Primer: Intermediate: Topcoat:
MPI 79 MPI 164 MPI 164
System DFT: 125 microns (5 mils)]]

K. Hot metal surfaces [including smokestacks] subject to temperatures up to
205 degrees C (400 degrees F):

1. [Heat Resistant Enamel
MPI EXT 5.2A
Primer: Intermediate: Topcoat:
MPI 21 Surface preparation and number of coats per

manufacturer's instructions.
System DFT: Per Manufacturer]

L. Ferrous metal subject to high temperature, up to 400 degrees C (750 degrees F):

1. [Inorganic Zinc Rich Coating
MPI EXT 5.2C
Primer: Intermediate: Topcoat:
MPI 19 Surface preparation and number of coats per
manufacturer's instructions.
System DFT: Per Manufacturer]

2. [Heat Resistant Aluminum Enamel
MPI EXT 5.2B (Aluminum Finish)
Primer: Intermediate: Topcoat:
MPI 2 Surface preparation and number of coats per
manufacturer's instructions.
System DFT: Per Manufacturer]

M. [New surfaces][and][Existing surfaces] made bare cleaning to SSPC SP 10/NACE No. 2
subject to temperatures up to 593 degrees C (1100 degrees F):

1. [Heat Resistant Coating
MPI EXT 5.2D
Primer: Intermediate: Topcoat:
MPI 22 Surface preparation and number of coats per
manufacturer's instructions.
System DFT: Per Manufacturer]

DIVISION 6: EXTERIOR WOOD; DRESSED LUMBER, PANELING, DECKING, SHINGLES PAINT TABLE

A. New [and Existing, uncoated] Dressed lumber, Wood and plywood, trim,
[including top, bottom and edges of doors] not otherwise specified:

1. [Alkyd
[MPI EXT 6.3B-G5 (Semigloss)
Primer: Intermediate: Topcoat:
MPI 7 MPI 94 MPI 94
System DFT: 125 microns (5 mils)]

[MPI EXT 6.3B-G6 (Gloss)
Primer: Intermediate: Topcoat:
MPI 7 MPI 9 MPI 9
System DFT: 125 microns (5 mils)]]

2. [Latex
[MPI EXT 6.3A-G1 (Flat)
Primer: Intermediate: Topcoat:
MPI 7 MPI 10 MPI 10
System DFT: 125 microns (5 mils)]

[MPI EXT 6.3A-G5 (Semigloss)
Primer: Intermediate: Topcoat:
MPI 7 MPI 11 MPI 11

System DFT: 125 microns (5 mils)]

[MPI EXT 6.3A-G6 (Gloss)

Primer: Intermediate: Topcoat:
MPI 7 MPI 119 MPI 119

System DFT: 125 microns (5 mils)]]

3. [Waterborne Solid Color Stain

MPI EXT 6.3K

Primer: Intermediate: Topcoat:
MPI 7 MPI 16 MPI 16

System DFT: 106 microns (4.25 mils)]

B. Existing, dressed lumber, Wood and plywood, trim, [including top, bottom and edges of doors] previously coated with an alkyd / oil based finish coat not otherwise specified:

1. [Alkyd

[MPI REX 6.3B-G5 (Semigloss)

Primer: Intermediate: Topcoat:
MPI 5 MPI 94 MPI 94

System DFT: 125 microns (5 mils)]

[MPI REX 6.3B-G6 (Gloss)

Primer: Intermediate: Topcoat:
MPI 5 MPI 9 MPI 9

System DFT: 125 microns (5 mils)]]

2. [Latex

[MPI REX 6.3A-G1 (Flat)

Primer: Intermediate: Topcoat:
MPI 5 MPI 10 MPI 10

System DFT: 125 microns (5 mils)]

[MPI REX 6.3A-G5 (Semigloss)

Primer: Intermediate: Topcoat:
MPI 5 MPI 11 MPI 11

System DFT: 125 microns (5 mils)]

[MPI REX 6.3A-G6 (Gloss)

Primer: Intermediate: Topcoat:
MPI 5 MPI 119 MPI 119

System DFT: 125 microns (5 mils)]]

C. Existing, dressed lumber, Wood and plywood, trim, [including top, bottom and edges of doors] previously coated with a latex / waterborne finish coat not otherwise specified:

1. [Latex

[MPI REX 6.3L-G1 (Flat)

Spot Primer: Intermediate: Topcoat:
MPI 6 MPI 10 MPI 10

System DFT: 112 microns (4.5 mils)]

[MPI REX 6.3L-G5 (Semigloss)

Spot Primer: Intermediate: Topcoat:
MPI 6 MPI 11 MPI 11

- System DFT: 112 microns (4.5 mils)]
- [MPI REX 6.3L-G6 (Gloss)
Spot Primer: Intermediate: Topcoat:
MPI 6 MPI 119 MPI 119
System DFT: 112 microns (4.5 mils)]]
2. [Waterborne Solid Color Stain
MPI REX 6.3K (Stain)
Spot Primer: Intermediate: Topcoat:
MPI 6 MPI 16 MPI 16
System DFT: 100 microns (4 mils)]
- D. New, Uncoated wood siding:
1. [Semi-Transparent Stain
MPI EXT 6.3D
Spot Primer: Intermediate: Topcoat:
N/A MPI 13 MPI 13
System DFT: N/A]
- E. Existing, previously stained wood siding:
1. [Latex
[MPI REX 6.2K-G1 (Flat)
Primer: Intermediate: Topcoat:
MPI 5 MPI 10 MPI 10
System DFT: 112 microns (4.5 mils)]
- [MPI REX 6.2K-G5 (Semigloss)
Primer: Intermediate: Topcoat:
MPI 5 MPI 11 MPI 11
System DFT: 112 microns (4.5 mils)]]
- F. Existing Uncoated or previously semitransparent stained wood siding:
1. [Semi-Transparent Stain
MPI REX 6.3D
Spot Primer: Intermediate: Topcoat:
N/A MPI 13 MPI 13
System DFT: Per Manufacturer]
- G. Wood: [Steps,] [platforms,] [floors of open porches,] and [_____] [with non-skid additive (NSA), load at manufacturer's recommendations.]:
1. [Latex Floor Paint
[MPI EXT 6.5A-G2 (Flat)
Primer: Intermediate: Topcoat:
MPI 5 MPI 60 [plus NSA] MPI 60 [plus NSA]
System DFT: 112 microns (4.5 mils)]
- [MPI EXT 6.5A-G6 (Gloss)
Primer: Intermediate: Topcoat:
MPI 5 MPI 68 [plus NSA] MPI 68 [plus NSA]
System DFT: 112 microns (4.5 mils)]]
2. [Alkyd Floor Paint

[MPI EXT 6.5B-G2 (Flat)
Primer: Intermediate: Topcoat:
MPI 59 MPI 59 [plus NSA] MPI 59 [plus NSA]
System DFT: 125 microns (5 mils)]

[MPI EXT 6.5B-G6 (Gloss)
Primer: Intermediate: Topcoat:
MPI 27 MPI 27 [plus NSA] MPI 27 [plus NSA]
System DFT: 125 microns (5 mils)]

DIVISION 9: EXTERIOR STUCCO PAINT TABLE

A. [New] [and Existing] stucco:

1. [Latex

[New; MPI EXT 9.1A-G1 (Flat) / Existing; MPI REX 9.1A-G2 (Flat)
Primer: Intermediate: Topcoat:
MPI 10 MPI 10 MPI 10
System DFT: 112 microns (4.5 mils)]

[New; MPI EXT 9.1A-G5 (Semigloss) / Existing; MPI REX 9.1A-G5 (Semigloss)
Primer: Intermediate: Topcoat:
MPI 11 MPI 11 MPI 11
System DFT: 112 microns (4.5 mils)]

[New; MPI EXT 9.1A-G6 (Gloss) / Existing; MPI REX 9.1A-G6 (Gloss)
Primer: Intermediate: Topcoat:
MPI 119 MPI 119 MPI 119
System DFT: 112 microns (4.5 mils)]

Primer as recommended by manufacturer. Topcoat: Coating to match adjacent surfaces. On existing stucco, apply primer based on surface condition.]

B. [New] [and Existing] stucco, elastomeric system:

1. [Elastomeric Coating

New; MPI EXT 9.1C / Existing; MPI REX 9.1C
Primer: Intermediate: Topcoat:
N/A MPI 113 MPI 113
System DFT: 400 microns (16 mils)

Primer as recommended by manufacturer. Topcoat: Coating to match adjacent surfaces. Surface preparation and number of coats in accordance with manufacturer's instructions).

NOTE: Apply sufficient coats of MPI 113 to achieve a minimum dry film thickness of 400 microns (16 mils).]

DIVISION 10: EXTERIOR CLOTH COVERINGS AND BITUMINOUS COATED SURFACES PAINT TABLE

A. Insulation and surfaces of insulation coverings (canvas, cloth, paper):
(Interior and Exterior Applications)

1. [Latex

[MPI EXT 10.1A-G1 (Flat)
Primer: Intermediate: Topcoat:
N/A MPI 10 MPI 10
System DFT: 80 microns (3.2 mils)]

[MPI EXT 10.1A-G5 (Semigloss)
Primer: Intermediate: Topcoat:
N/A MPI 11 MPI 11
System DFT: 80 microns (3.2 mils)]

[MPI EXT 10.1A-G6 (Gloss)
Primer: Intermediate: Topcoat:
N/A MPI 119 MPI 119
System DFT: 80 microns (3.2 mils)]

Topcoat: Coating to match adjacent surfaces.]

3.15.2 Interior Paint Tables

DIVISION 3: INTERIOR CONCRETE PAINT TABLE

A. [New and uncoated existing] [and Existing, previously painted] Concrete, vertical surfaces, not specified otherwise:

1. [Latex

[New; MPI INT 3.1A-G2 (Flat) / Existing; MPI RIN 3.1A-G2 (Flat)

Primer: Intermediate: Topcoat:
MPI 50 MPI 44 MPI 44
System DFT: 100 microns (4 mils)]

[New; MPI INT 3.1A-G3 (Eggshell) / Existing; MPI RIN 3.1A-G3 (Eggshell)

Primer: Intermediate: Topcoat:
MPI 50 MPI 52 MPI 52
System DFT: 100 microns (4 mils)]

[New; MPI INT 3.1A-G5 (Semigloss) / Existing; MPI RIN 3.1A-G5 (Semigloss)

Primer: Intermediate: Topcoat:
MPI 50 MPI 54 MPI 54
System DFT: 100 microns (4 mils)]]

2. [High Performance Architectural Latex

[New; MPI INT 3.1C-G2 (Flat) / Existing; MPI RIN 3.1J-G2 (Flat)

Primer: Intermediate: Topcoat:
MPI 50 MPI 138 MPI 138
System DFT: 100 microns (4 mils)]

[New; MPI INT 3.1C-G3 (Eggshell) / Existing; MPI RIN 3.1J-G3 (Eggshell)

Primer: Intermediate: Topcoat:
MPI 50 MPI 139 MPI 139
System DFT: 100 microns (4 mils)]

[New; MPI INT 3.1C-G4 (satin) / Existing; MPI RIN 3.1J-G4

Primer: Intermediate: Topcoat:
MPI 50 MPI 140 MPI 140
System DFT: 100 microns (4 mils)]

[New; MPI INT 3.1C-G5 (Semigloss) / Existing; MPI RIN 3.1J-G5 (Semigloss)

Primer: Intermediate: Topcoat:
MPI 50 MPI 141 MPI 141
System DFT: 100 microns (4 mils)]]

3. [Institutional Low Odor / Low VOC Latex
[New; MPI INT 3.1M-G2 (Flat) / Existing; MPI RIN 3.1L-G2 (Flat)

Primer: Intermediate: Topcoat:
MPI 50 MPI 144 MPI 144
System DFT: 100 microns (4 mils)]

[New; MPI INT 3.1M-G3 (Eggshell) / Existing; MPI RIN 3.1L-G3 (Eggshell)

Primer: Intermediate: Topcoat:
MPI 50 MPI 145 MPI 145
System DFT: 100 microns (4 mils)]

[New; MPI INT 3.1M-G4 (satin) / Existing; MPI RIN 3.1L-G4

Primer: Intermediate: Topcoat:
MPI 50 MPI 146 MPI 146
System DFT: 100 microns (4 mils)]

[New; MPI INT 3.1M-G5 (Semigloss) / Existing; MPI RIN 3.1L-G5 (Semigloss)

Primer: Intermediate: Topcoat:
MPI 50 MPI 147 MPI 147
System DFT: 100 microns (4 mils)]]

B. Concrete ceilings, uncoated:

1. [Latex Aggregate

MPI INT 3.1N

Primer: Intermediate: Topcoat:
N/A N/A MPI 42

System DFT: Per Manufacturer

Texture - [Fine] [Medium] [Coarse]. Surface preparation, number of coats, and primer in accordance with manufacturer's instructions.

Topcoat: Coating to match adjacent surfaces.]

C. [New and uncoated existing][and][Existing, previously painted] Concrete in [toilets,] [food-preparation,] [food-serving,] [restrooms,] [laundry areas,] [shower areas,] [areas requiring a high degree of sanitation,] [_____] [and other high-humidity areas] not otherwise specified except floors:

1. [Waterborne Light Industrial Coating

[New; MPI INT 3.1L-G3(Eggshell) / Existing; MPI RIN 3.1C-G3(Eggshell)

Primer: Intermediate: Topcoat:
MPI 151 MPI 151 MPI 151

System DFT: 120 microns (4.8 mils)]

[New; MPI INT 3.1L-G5(Semigloss) / Existing; MPI RIN 3.1C-G5(Semigloss)

Primer: Intermediate: Topcoat:
MPI 153 MPI 153 MPI 153

System DFT: 120 microns (4.8 mils)]

[New; MPI INT 3.1L-G6(Gloss) / Existing; MPI RIN 3.1C-G6(Gloss)

Primer: Intermediate: Topcoat:
MPI 154 MPI 154 MPI 154

System DFT: 120 microns (4.8 mils)]]

2. [Alkyd
[New; MPI INT 3.1D-G3 (Eggshell) / Existing; RIN 3.1D-G3 (Eggshell)
Primer: Intermediate: Topcoat:
MPI 50 MPI 51 MPI 51
System DFT: 112 microns (4.5 mils)]

[MPI INT 3.1D-G5 (Semigloss) / Existing; RIN 3.1D-G5 (Semigloss)
Primer: Intermediate: Topcoat:
MPI 50 MPI 47 MPI 47
System DFT: 112 microns (4.5 mils)]

[MPI INT 3.1D-G6 (Gloss) / Existing; RIN 3.1D-G6 (Gloss)
Primer: Intermediate: Topcoat:
MPI 50 MPI 48 MPI 48
System DFT: 112 microns (4.5 mils)]]

3. [Epoxy
New; MPI INT 3.1F-G6 (Gloss) / Existing; MPI RIN 3.1E-G6 (Gloss)
Primer: Intermediate: Topcoat:
MPI 77 MPI 77 MPI 77
System DFT: 100 microns (4 mils)

Note: Primer may be reduced for penetration per manufacturer's instructions.]

- D. [New and uncoated existing] [and Existing, previously painted] concrete walls and bottom of swimming pools:

1. [Chlorinated Rubber
Primer: Intermediate: Topcoat:
SSPC Paint 18 SSPC Paint 18 SSPC Paint 18
System DFT: Per Manufacturer

Note: Primer may be reduced for penetration per manufacturer's instructions.]

2. [Epoxy
New; MPI INT 3.1F / Existing; MPI RIN 3.1E
Primer: Intermediate: Topcoat:
MPI 77 MPI 77 MPI 77
System DFT: 100 microns (4 mils)

Note: Primer may be reduced for penetration per manufacturer's instructions.]

- E. [[New and uncoated existing] [and Existing, previously painted] concrete floors in following areas [_____]:

1. [Latex Floor Paint
New; MPI INT 3.2A-G2 (Flat) / Existing; MPI RIN 3.2A-G2 (Flat)
Primer: Intermediate: Topcoat:
MPI 60 MPI 60 MPI 60
System DFT: 125 microns (5 mils)]

2. [Alkyd Floor Paint

New; MPI INT 3.2B-G2 (Flat) / Existing; MPI RIN 3.2B-G2 (Flat)
 Primer: Intermediate: Topcoat:
 MPI 59 MPI 59 MPI 59
 System DFT: 125 microns (5 mils)]

3. [Epoxy
 New; MPI INT 3.2C-G6 (Gloss) / Existing; MPI RIN 3.2C-G6 (Gloss)
 Primer: Intermediate: Topcoat:
 MPI 77 MPI 77 MPI 77
 System DFT: 125 microns (5 mils)]

Note: Primer may be reduced for penetration per manufacturer's instructions.]

DIVISION 4: INTERIOR CONCRETE MASONRY UNITS PAINT TABLE

A. New [and uncoated Existing] Concrete masonry:

1. [High Performance Architectural Latex
 [MPI INT 4.2D-G2 (Flat)
 Filler Primer: Intermediate: Topcoat:
 MPI 4 N/A MPI 138 MPI 138
 System DFT: 275 microns (11 mils)]

 [MPI INT 4.2D-G3 (Eggshell)
 Filler Primer: Intermediate: Topcoat:
 MPI 4 N/A MPI 139 MPI 139
 System DFT: 275 microns (11 mils)]

 [MPI INT 4.2D-G4 (Satin)
 Filler Primer: Intermediate: Topcoat:
 MPI 4 N/A MPI 140 MPI 140
 System DFT: 275 microns (11 mils)]

 [MPI INT 4.2D-G5 (Semigloss)
 Filler Primer: Intermediate: Topcoat:
 MPI 4 N/A MPI 141 MPI 141
 System DFT: 275 microns (11 mils)]

Fill all holes in masonry surface]

2. [Institutional Low Odor / Low VOC Latex
 [New; MPI INT 4.2E-G2 (Flat)
 Filler Primer: Intermediate: Topcoat:
 MPI 4 N/A MPI 144 MPI 144
 System DFT: 100 microns (4 mils)]

 [New; MPI INT 4.2E-G3 (Eggshell)
 Filler Primer: Intermediate: Topcoat:
 MPI 4 N/A MPI 145 MPI 145
 System DFT: 100 microns (4 mils)]

 [New; MPI INT 4.2E-G4 (Satin)
 Filler Primer: Intermediate: Topcoat:
 MPI 4 N/A MPI 146 MPI 146
 System DFT: 100 microns (4 mils)]

[New; MPI INT 4.2E-G5 (Semigloss)
Filler Primer: Intermediate: Topcoat:
MPI 4 N/A MPI 147 MPI 147
System DFT: 100 microns (4 mils)]]

B. Existing, previously painted Concrete masonry:

1. [High Performance Architectural Latex
[MPI RIN 4.2K-G2 (Flat)
Spot Primer: Intermediate: Topcoat:
MPI 50 MPI 138 MPI 138
System DFT: 112 microns (4.5 mils)]

[MPI RIN 4.2K-G3 (Eggshell)
Spot Primer: Intermediate: Topcoat:
MPI 50 MPI 139 MPI 139
System DFT: 112 microns (4.5 mils)]

[MPI RIN 4.2K-G4
Spot Primer: Intermediate: Topcoat:
MPI 50 MPI 140 MPI 140
System DFT: 112 microns (4.5 mils)]

[MPI RIN 4.2K-G5 (Semigloss)
Spot Primer: Intermediate: Topcoat:
MPI 50 MPI 141 MPI 141
System DFT: 112 microns (4.5 mils)]]

2. [Institutional Low Odor / Low VOC Latex
[Existing; MPI RIN 4.2L-G2 (Flat)
Spot Primer: Intermediate: Topcoat:
MPI 50 MPI 144 MPI 144
System DFT: 100 microns (4 mils)]

[Existing; MPI RIN 4.2L-G3 (Eggshell)
Spot Primer: Intermediate: Topcoat:
MPI 50 MPI 145 MPI 145
System DFT: 100 microns (4 mils)]

[Existing; MPI RIN 4.2L-G4 (Satin)
Spot Primer: Intermediate: Topcoat:
MPI 50 MPI 146 MPI 146
System DFT: 100 microns (4 mils)]

[Existing; MPI RIN 4.2L-G5 (Semigloss)
Spot Primer: Intermediate: Topcoat:
MPI 50 MPI 147 MPI 147
System DFT: 100 microns (4 mils)]]

C. New [and uncoated Existing] Concrete masonry units in [toilets,]
[food-preparation,] [food-serving,] [restrooms,] [laundry areas,] [shower
areas,] [areas requiring a high degree of sanitation,] [_____,] [and
other high humidity areas] unless otherwise specified:

1. [Waterborne Light Industrial Coating
[MPI INT 4.2K-G3 (Eggshell)

Filler: Primer: Intermediate: Topcoat:
MPI 4 N/A MPI 151 MPI 151
System DFT: 275 microns (11 mils)]

[MPI INT 4.2K-G5 (Semigloss)
Filler: Primer: Intermediate: Topcoat:
MPI 4 N/A MPI 153 MPI 153
System DFT: 275 microns (11 mils)]

[MPI INT 4.2K-G6 (Gloss)
Filler: Primer: Intermediate: Topcoat:
MPI 4 N/A MPI 154 MPI 154
System DFT: 275 microns (11 mils)]

Fill all holes in masonry surface]

2. [Alkyd
[MPI INT 4.2N-G3 (Eggshell)
Filler: Primer: Intermediate: Topcoat:
MPI 4 MPI 50 MPI 51 MPI 51
System DFT: 300 microns (12 mils)]

[MPI INT 4.2N-G5 (Semigloss)
Filler: Primer: Intermediate: Topcoat:
MPI 4 MPI 50 MPI 47 MPI 47
System DFT: 300 microns (12 mils)]

[MPI INT 4.2N-G6 (Gloss)
Filler: Primer: Intermediate: Topcoat:
MPI 4 MPI 50 MPI 48 MPI 48
System DFT: 300 microns (12 mils)]

Fill all holes in masonry surface]

3. [Epoxy
MPI INT 4.2G-G6 (Gloss)
Filler: Primer: Intermediate: Topcoat:
MPI 116 N/A MPI 77 MPI 77
System DFT: 250 microns (10 mils)

Fill all holes in masonry surface]

D. Existing, previously painted, concrete masonry units in [toilets,]
[food-preparation,] [food-serving,] [restrooms,] [laundry areas,] [shower
areas,] [areas requiring a high degree of sanitation,] [_____,] [and
other high humidity areas] unless otherwise specified:

1. [Waterborne Light Industrial Coating
[MPI RIN 4.2G-G3 (Eggshell)
Spot Primer: Intermediate: Topcoat:
MPI 151 MPI 151 MPI 151
System DFT: 112 microns (4.5 mils)]

[MPI RIN 4.2G-G5 (Semigloss)
Spot Primer: Intermediate: Topcoat:
MPI 153 MPI 153 MPI 153
System DFT: 112 microns (4.5 mils)]

[MPI RIN 4.2G-G6 (Gloss)
Spot Primer: Intermediate: Topcoat:
MPI 154 MPI 154 MPI 154
System DFT: 112 microns (4.5 mils)]]

2. [Alkyd
[MPI RIN 4.2C-G3 (Eggshell)
Spot Primer: Intermediate: Topcoat:
MPI 50 MPI 51 MPI 51
System DFT: 112 microns (4.5 mils)]

[MPI RIN 4.2C-G5 (Semigloss)
Spot Primer: Intermediate: Topcoat:
MPI 50 MPI 47 MPI 47
System DFT: 112 microns (4.5 mils)]

[MPI RIN 4.2C-G6 (Gloss)
Spot Primer: Intermediate: Topcoat:
MPI 50 MPI 48 MPI 48
System DFT: 112 microns (4.5 mils)]]

3. [Epoxy
MPI RIN 4.2D-G6 (Gloss)
Spot Primer: Intermediate: Topcoat:
MPI 77 MPI 77 MPI 77
System DFT: 125 microns (5 mils)]

DIVISION 5: INTERIOR METAL, FERROUS AND NON-FERROUS PAINT TABLE

INTERIOR STEEL / FERROUS SURFACES

A. Metal, [Mechanical,] [Electrical,] [Fire extinguishing sprinkler systems including valves, conduit, hangers, supports,] [Surfaces adjacent to painted surfaces (Match surrounding finish),] [exposed copper piping,] [and miscellaneous metal items] not otherwise specified except floors, hot metal surfaces, and new prefinished equipment:

1. [High Performance Architectural Latex
[MPI INT 5.1R-G2 (Flat)
Primer: Intermediate: Topcoat:
MPI 79 MPI 138 MPI 138
System DFT: 125 microns (5 mils)]

[MPI INT 5.1R-G3 (Eggshell)
Primer: Intermediate: Topcoat:
MPI 79 MPI 139 MPI 139
System DFT: 125 microns (5 mils)]

[MPI INT 5.1R-G5 (Semigloss)
Primer: Intermediate: Topcoat:
MPI 79 MPI 141 MPI 141
System DFT: 125 microns (5 mils)]]

2. [Alkyd
[MPI INT 5.1E-G2 (Flat)
Primer: Intermediate: Topcoat:

MPI 79 MPI 49 MPI 49
System DFT: 131 microns (5.25 mils)]

[MPI INT 5.1E-G3 (Eggshell)
Primer: Intermediate: Topcoat:
MPI 79 MPI 51 MPI 51
System DFT: 131 microns (5.25 mils)]

[MPI INT 5.1E-G5 (Semigloss)
Primer: Intermediate: Topcoat:
MPI 79 MPI 47 MPI 47
System DFT: 131 microns (5.25 mils)]

[MPI INT 5.1E-G6 (Gloss)
Primer: Intermediate: Topcoat:
MPI 79 MPI 48 MPI 48
System DFT: 131 microns (5.25 mils)]]

B. Metal floors (non-shop-primed surfaces or non-slip deck surfaces) with non-skid additive (NSA), load at manufacturer's recommendations.:

1. [Alkyd Floor Paint
MPI INT 5.1U-G6 (Gloss)
Primer: Intermediate: Topcoat:
MPI 79 MPI 27 MPI 27 (plus NSA)
System DFT: 131 microns (5.25 mils)]

2. [Epoxy
MPI INT 5.1L-G6 (Gloss)
Primer: Intermediate: Topcoat:
MPI 101 MPI 77 MPI 77 (plus NSA)
System DFT: 131 microns (5.25 mils)]

C. Metal in [toilets,] [food-preparation,] [food-serving,] [restrooms,] [laundry areas,] [shower areas,] [areas requiring a high degree of sanitation,] [_____,] [and other high-humidity areas] not otherwise specified except floors, hot metal surfaces, and new prefinished equipment:

1. [Alkyd
[MPI INT 5.1E-G3 (Eggshell)
Primer: Intermediate: Topcoat:
MPI 79 MPI 51 MPI 51
System DFT: 131 microns (5.25 mils)]

[MPI INT 5.1E-G5 (Semigloss)
Primer: Intermediate: Topcoat:
MPI 79 MPI 47 MPI 47
System DFT: 131 microns (5.25 mils)]

[MPI INT 5.1E-G6 (Gloss)
Primer: Intermediate: Topcoat:
MPI 79 MPI 48 MPI 48
System DFT: 131 microns (5.25 mils)]]

2. [Alkyd
[MPI INT 5.1T-G3 (Eggshell) For hand tool cleaning
Primer: Intermediate: Topcoat:

MPI 23 MPI 51 MPI 51
System DFT: 131 microns (5.25 mils)]

[MPI INT 5.1T-G5 (Semigloss)
Primer: Intermediate: Topcoat:
MPI 23 MPI 47 MPI 47
System DFT: 131 microns (5.25 mils)]

[MPI INT 5.1T-G6 (Gloss)
Primer: Intermediate: Topcoat:
MPI 23 MPI 48 MPI 48
System DFT: 131 microns (5.25 mils)]]

D. Ferrous metal in concealed damp spaces or in exposed areas having unpainted adjacent surfaces as follows: [_____]

1. [Aluminum Paint
MPI INT 5.1M
Primer: Intermediate: Topcoat:
MPI 79 MPI 1 MPI 1
System DFT: 106 microns (4.25 mils)]

E. Miscellaneous non-ferrous metal items not otherwise specified except floors, hot metal surfaces, and new prefinished equipment. Match surrounding finish:

1. [High Performance Architectural Latex
[MPI INT 5.4F-G2 (Flat)
Primer: Intermediate: Topcoat:
MPI 95 MPI 138 MPI 138
System DFT: 125 microns (5 mils)]

[MPI INT 5.4F-G3 (Eggshell)
Primer: Intermediate: Topcoat:
MPI 95 MPI 139 MPI 139
System DFT: 125 microns (5 mils)]

[MPI INT 5.4F-G4 (Satin)
Primer: Intermediate: Topcoat:
MPI 95 MPI 140 MPI 140
System DFT: 125 microns (5 mils)]

[MPI INT 5.4F-G5 (Semigloss)
Primer: Intermediate: Topcoat:
MPI 95 MPI 141 MPI 141
System DFT: 125 microns (5 mils)]]

2. [Alkyd
[MPI INT 5.4J-G2 (Flat)
Primer: Intermediate: Topcoat:
MPI 95 MPI 49 MPI 49
System DFT: 125 microns (5 mils)]

[MPI INT 5.4J-G3 (Eggshell)
Primer: Intermediate: Topcoat:
MPI 95 MPI 51 MPI 51
System DFT: 125 microns (5 mils)]

[MPI INT 5.4J-G5 (Semigloss)
Primer: Intermediate: Topcoat:
MPI 95 MPI 47 MPI 47
System DFT: 125 microns (5 mils)]

[MPI INT 5.4J-G6 (Gloss)
Primer: Intermediate: Topcoat:
MPI 95 MPI 48 MPI 48
System DFT: 125 microns (5 mils)]]

F. Hot metal surfaces [including smokestacks] subject to temperatures up to 205 degrees C (400 degrees F):

1. [Heat Resistant Enamel
MPI INT 5.2A
Primer: Intermediate: Topcoat:
MPI 21 Surface preparation and number of coats per
manufacturer's instructions.
System DFT: Per Manufacturer]

G. Ferrous metal subject to high temperature, up to 400 degrees C (750 degrees F):

1. [Inorganic Zinc Rich Coating
MPI INT 5.2C
Primer: Intermediate: Topcoat:
MPI 19 Surface preparation and number of coats per
manufacturer's instructions.
System DFT: Per Manufacturer]
2. [Heat Resistant Aluminum Paint
MPI INT 5.2B (Aluminum Finish)
Primer: Intermediate: Topcoat:
MPI 2 Surface preparation and number of coats per
manufacturer's instructions.
System DFT: Per Manufacturer]

H. [New surfaces and] [Existing surfaces] made bare cleaning to SSPC SP 10/NACE No. 2
subject to temperatures up to 593 degrees C (1100 degrees F):

1. [High Heat Resistant Coating
MPI INT 5.2D
Primer: Intermediate: Topcoat:
MPI 22 Surface preparation and number of coats per
manufacturer's instructions.
System DFT: Per Manufacturer]

DIVISION 6: INTERIOR WOOD PAINT TABLE

A. New [and Existing, uncoated] Wood and plywood not otherwise specified:

1. [High Performance Architectural Latex
[MPI INT 6.4S-G3 (Eggshell)
Primer: Intermediate: Topcoat:
MPI 39 MPI 139 MPI 139

System DFT: 112 microns (4.5 mils)]

[MPI INT 6.4S-G4 (Satin)

Primer: Intermediate: Topcoat:
MPI 39 MPI 140 MPI 140

System DFT: 112 microns (4.5 mils)]

[MPI INT 6.4S-G5 (Semigloss)

Primer: Intermediate: Topcoat:
MPI 39 MPI 141 MPI 141

System DFT: 112 microns (4.5 mils)]]

2. [Alkyd

[MPI INT 6.4B-G3 (Eggshell)

Primer: Intermediate: Topcoat:
MPI 45 MPI 51 MPI 51

System DFT: 112 microns (4.5 mils)]

[MPI INT 6.4B-G5 (Semigloss)

Primer: Intermediate: Topcoat:
MPI 45 MPI 47 MPI 47

System DFT: 112 microns (4.5 mils)]

[MPI INT 6.4B-G6 (Gloss)

Primer: Intermediate: Topcoat:
MPI 45 MPI 48 MPI 48

System DFT: 112 microns (4.5 mils)]]

3. [Institutional Low Odor / Low VOC Latex

[New; MPI INT 6.3V-G2 (Flat)

Primer: Intermediate: Topcoat:
MPI 39 MPI 144 MPI 144

System DFT: 100 microns (4 mils)]

[New; MPI INT 6.3V-G3 (Eggshell)

Primer: Intermediate: Topcoat:
MPI 39 MPI 145 MPI 145

System DFT: 100 microns (4 mils)]

[New; MPI INT 6.3V-G4

Primer: Intermediate: Topcoat:
MPI 39 MPI 146 MPI 146

System DFT: 100 microns (4 mils)]

[New; MPI INT 6.3V-G5 (Semigloss)

Primer: Intermediate: Topcoat:
MPI 39 MPI 147 MPI 147

System DFT: 100 microns (4 mils)]]

B. Existing, previously painted Wood and plywood not otherwise specified:

1. [High Performance Architectural Latex

[MPI RIN 6.4B-G3 (Eggshell)

Primer: Intermediate: Topcoat:
MPI 46 MPI 139 MPI 139

System DFT: 1123 microns (4.5 mils)]

[MPI RIN 6.4B-G4 (Satin)
Primer: Intermediate: Topcoat:
MPI 46 MPI 140 MPI 140
System DFT: 112 microns (4.5 mils)]

[MPI RIN 6.4B-G5 (Semigloss)
Primer: Intermediate: Topcoat:
MPI 46 MPI 141 MPI 141
System DFT: 112 microns (4.5 mils)]]

2. [Alkyd

[MPI RIN 6.4C-G3 (Eggshell)
Primer: Intermediate: Topcoat:
MPI 46 MPI 51 MPI 51
System DFT: 112 microns (4.5 mils)]

[MPI RIN 6.4C-G5 (Semigloss)
Primer: Intermediate: Topcoat:
MPI 46 MPI 47 MPI 47
System DFT: 112 microns (4.5 mils)]

[MPI RIN 6.4C-G6 (Gloss)
Primer: Intermediate: Topcoat:
MPI 46 MPI 48 MPI 48
System DFT: 112 microns (4.5 mils)]]

3. [Institutional Low Odor / Low VOC Latex

[Existing; MPI RIN 6.4D-G2 (Flat)
Primer: Intermediate: Topcoat:
MPI 39 MPI 144 MPI 144
System DFT: 100 microns (4 mils)]

[Existing; MPI RIN 6.4D-G3 (Eggshell)
Primer: Intermediate: Topcoat:
MPI 39 MPI 145 MPI 145
System DFT: 100 microns (4 mils)]

[Existing; MPI RIN 6.4D-G4
Primer: Intermediate: Topcoat:
MPI 39 MPI 146 MPI 146
System DFT: 100 microns (4 mils)]

[Existing; MPI RIN 6.4D-G5 (Semigloss)
Primer: Intermediate: Topcoat:
MPI 39 MPI 147 MPI 147
System DFT: 100 microns (4 mils)]]

C. New [and Existing, previously finished or stained] Wood and Plywood,
except floors; natural finish or stained:

1. [Natural finish, oil-modified polyurethane

[New; MPI INT 6.4J-G4 / Existing; MPI RIN 6.4L-G4
Primer: Intermediate: Topcoat:
MPI 57 MPI 57 MPI 57
System DFT: 100 microns (4 mils)]

[New; MPI INT 6.4J-G6 (Gloss) / Existing; MPI RIN 6.4L-G6 (Gloss)

Primer: Intermediate: Topcoat:
MPI 56 MPI 56 MPI 56
System DFT: 100 microns (4 mils)]]

2. [Stained, oil-modified polyurethane
[New; MPI INT 6.4E-G4 / Existing; MPI RIN 6.4G-G4
Stain: Primer: Intermediate: Topcoat:
MPI 90 MPI 57 MPI 57 MPI 57
System DFT: 100 microns (4 mils)]

[New; MPI INT 6.4E-G6 (Gloss) / Existing; MPI RIN 6.4G-G6 (Gloss)
Stain: Primer: Intermediate: Topcoat:
MPI 90 MPI 56 MPI 56 MPI 56
System DFT: 100 microns (4 mils)]]

3. [Stained, Moisture Cured Urethane
[New; MPI INT 6.4V-G2 (Flat) / Existing; MPI RIN 6.4V-G2 (Flat)
Stain: Primer: Intermediate: Topcoat:
MPI 90 MPI 71 MPI 71 MPI 71
System DFT: 100 microns (4 mils)]

[New; MPI INT 6.4V-G6 (Gloss) / Existing; MPI RIN 6.4V-G6 (Gloss)
Stain: Primer: Intermediate: Topcoat:
MPI 90 MPI 31 MPI 31 MPI 31
System DFT: 100 microns (4 mils)]]

D. New [and Existing, previously finished or stained] Wood Floors; Natural finish or stained:

1. [Natural finish, oil-modified polyurethane
New; MPI INT 6.5C-G6 (Gloss) / Existing; MPI RIN 6.5C-G6 (Gloss)
Primer: Intermediate: Topcoat:
MPI 56 MPI 56 MPI 56
System DFT: 100 microns (4 mils)]

2. [Natural finish, Moisture Cured Polyurethane
New; MPI INT 6.5K-G6 (Gloss) / Existing; MPI RIN 6.5D-G6 (Gloss)
Primer: Intermediate: Topcoat:
MPI 31 MPI 31 MPI 31
System DFT: 100 microns (4 mils)]

3. [Stained, oil-modified polyurethane
New; MPI INT 6.5B-G6 (Gloss) / Existing; MPI RIN 6.5B-G6 (Gloss)
Stain: Primer: Intermediate: Topcoat:
MPI 90 MPI 56 MPI 56 MPI 56
System DFT: 100 microns (4 mils)]

4. [Stained, Moisture Cured Polyurethane
New; MPI INT 6.5J-G6 (Gloss) / Existing; MPI RIN 6.5L-G6 (Gloss)
Stain: Primer: Intermediate: Topcoat:
MPI 90 MPI 31 MPI 31 MPI 31
System DFT: 100 microns (4 mils)]

E. New [and Existing, previously coated] Wood floors; pigmented finish:

1. [Latex Floor Paint
[New; MPI INT 6.5G-G2 (Flat) / Existing; MPI RIN 6.5J-G2 (Flat)

Primer: Intermediate: Topcoat:
MPI 45 MPI 60 MPI 60
System DFT: 112 microns (4.5 mils)]

[New; MPI INT 6.5G-G6 (Gloss) / Existing; MPI RIN 6.5J-G6 (Gloss)
Primer: Intermediate: Topcoat:
MPI 45 MPI 68 MPI 68
System DFT: 1123 microns (4.5 mils)]]

2. [Alkyd Floor Paint

[New; MPI INT 6.5A-G2 (Flat) / Existing; MPI RIN 6.5A-G2 (Flat)
Primer: Intermediate: Topcoat:
MPI 59 MPI 59 MPI 59
System DFT: 112 microns (4.5 mils)]

[New; MPI INT 6.5A-G6 (Gloss) / Existing; MPI RIN 6.5A-G6 (Gloss)
Primer: Intermediate: Topcoat:
MPI 27 MPI 27 MPI 27
System DFT: 112 microns (4.5 mils)]]

F. New [and Existing, uncoated] wood surfaces in [toilets,]
[food-preparation,] [food-serving,] [restrooms,] [laundry areas,] [shower
areas,] [areas requiring a high degree of sanitation,] [_____] [and
other high humidity areas] not otherwise specified.:

1. [As specified in Section 09 96 59 HIGH-BUILD GLAZE COATINGS.]

2. [Waterborne Light Industrial

[MPI INT 6.3P-G5 (Semigloss)
Primer: Intermediate: Topcoat:
MPI 45 MPI 153 MPI 153
System DFT: 112 microns (4.5 mils)]

[MPI INT 6.3P-G6 (Gloss)
Primer: Intermediate: Topcoat:
MPI 45 MPI 154 MPI 154
System DFT: 112 microns (4.5 mils)]]

3. [Alkyd

[MPI INT 6.3B-G5 (Semigloss)
Primer: Intermediate: Topcoat:
MPI 45 MPI 47 MPI 47
System DFT: 112 microns (4.5 mils)]

[MPI INT 6.3B-G6 (Gloss)
Primer: Intermediate: Topcoat:
MPI 45 MPI 48 MPI 48
System DFT: 112 microns (4.5 mils)]]

G. Existing, previously painted wood surfaces in [toilets,]
[food-preparation,] [food-serving,] [restrooms,] [laundry areas,] [shower
areas,] [areas requiring a high degree of sanitation,] [_____] [and
other high humidity areas] not otherwise specified:

1. [As specified in Section 09 96 59 HIGH-BUILD GLAZE COATINGS.]

2. [Waterborne Light Industrial Coating

[MPI RIN 6.3P-G5 (Semigloss)
Primer: Intermediate: Topcoat:
MPI 46 MPI 153 MPI 153
System DFT: 112 microns (4.5 mils)]

[MPI RIN 6.3P-G6 (Gloss)
Primer: Intermediate: Topcoat:
MPI 46 MPI 154 MPI 154
System DFT: 112 microns (4.5 mils)]]

3. [Alkyd
[MPI RIN 6.3B-G5 (Semigloss)
Primer: Intermediate: Topcoat:
MPI 46 MPI 47 MPI 47
System DFT: 112 microns (4.5 mils)]

[MPI RIN 6.3B-G6 (Gloss)
Primer: Intermediate: Topcoat:
MPI 46 MPI 48 MPI 48
System DFT: 112 microns (4.5 mils)]]

H. New [and Existing, previously finished or stained] Wood Doors; Natural Finish or Stained:

1. [Natural finish, oil-modified polyurethane
[New; MPI INT 6.3K-G4 / Existing; MPI RIN 6.3K-G4
Primer: Intermediate: Topcoat:
MPI 57 MPI 57 MPI 57
System DFT: 100 microns (4 mils)]

[New; MPI INT 6.3K-G6 (Gloss) / Existing; MPI RIN 6.3K-G6 (Gloss)
Primer: Intermediate: Topcoat:
MPI 56 MPI 56 MPI 56
System DFT: 100 microns (4 mils)]

Note: Sand between all coats per manufacturers recommendations.]

2. [Stained, oil-modified polyurethane
[New; MPI INT 6.3E-G4 / Existing; MPI RIN 6.3E-G4
Stain: Primer: Intermediate: Topcoat:
MPI 90 MPI 57 MPI 57 MPI 57
System DFT: 100 microns (4 mils)]

[New; MPI INT 6.3E-G6 (Gloss) / Existing; MPI RIN 6.3E-G6 (Gloss)
Stain: Primer: Intermediate: Topcoat:
MPI 90 MPI 56 MPI 56 MPI 56
System DFT: 100 microns (4 mils)]

Note: Sand between all coats per manufacturers recommendations.]

3. [Stained, Moisture Cured Urethane
[New; MPI INT 6.4V-G2 (Flat) / Existing; MPI RIN 6.4V-G2 (Flat)
Stain: Primer: Intermediate: Topcoat:
MPI 90 MPI 71 MPI 71 MPI 71
System DFT: 100 microns (4 mils)]

[New; MPI INT 6.4V-G6 (Gloss) / Existing; MPI RIN 6.4V-G6 (Gloss)

Stain: Primer: Intermediate: Topcoat:
MPI 90 MPI 31 MPI 31 MPI 31
System DFT: 100 microns (4 mils)]

Note: Sand between all coats per manufacturers recommendations.]

I. New [and Existing, uncoated] Wood Doors; Pigmented finish:

1. [Alkyd
[New; MPI INT 6.3B-G5 (Semigloss)
Primer: Intermediate: Topcoat:
MPI 45 MPI 47 MPI 47
System DFT: 112 microns (4.5 mils)]

[New; MPI INT 6.3B-G6 (Gloss)
Primer: Intermediate: Topcoat:
MPI 45 MPI 48 MPI 48
System DFT: 112 microns (4.5 mils)]

Note: Sand between all coats per manufacturers recommendations.]

2. [Pigmented Polyurethane
New; MPI INT 6.1E-G6 (Gloss)
Primer: Intermediate: Topcoat:
MPI 72 MPI 72 MPI 72
System DFT: 112 microns (4.5 mils)

Note: Sand between all coats per manufacturers recommendations.]

J. Existing, previously painted Wood Doors; Pigmented finish:

1. [Alkyd
[New; MPI RIN 6.3B-G5 (Semigloss)
Primer: Intermediate: Topcoat:
MPI 46 MPI 47 MPI 47
System DFT: 112 microns (4.5 mils)]

[New; MPI RIN 6.3B-G6 (Gloss)
Primer: Intermediate: Topcoat:
MPI 46 MPI 48 MPI 48
System DFT: 112 microns (4.5 mils)]

Note: Sand between all coats per manufacturers recommendations.]

DIVISION 9: INTERIOR PLASTER, GYPSUM BOARD, TEXTURED SURFACES PAINT
TABLE

A. New [and Existing, previously painted] [Plaster] [and] [Wallboard] not
otherwise specified:

1. [Latex
[New; MPI INT 9.2A-G2 (Flat) / Existing; RIN 9.2A-G2 (Flat)
Primer: Intermediate: Topcoat:
MPI 50 MPI 44 MPI 44
System DFT: 100 microns (4 mils)]

[New; MPI INT 9.2A-G3 (Eggshell) / Existing; RIN 9.2A-G3 (Eggshell)
Primer: Intermediate: Topcoat:
MPI 50 MPI 52 MPI 52
System DFT: 100 microns (4 mils)]

[New; MPI INT 9.2A-G5 (Semigloss) / Existing; RIN 9.2A-G5 (Semigloss)
Primer: Intermediate: Topcoat:
MPI 50 MPI 54 MPI 54
System DFT: 100 microns (4 mils)]]

2. [High Performance Architectural Latex - High Traffic Areas
[New; MPI INT 9.2B-G2 (Flat) / Existing; MPI RIN 9.2B-G2 (Flat)
Primer: Intermediate: Topcoat:
MPI 50 MPI 138 MPI 138
System DFT: 100 microns (4 mils)]

[New; MPI INT 9.2B-G3 (Eggshell) / Existing; MPI RIN 9.2B-G3 (Eggshell)
Primer: Intermediate: Topcoat:
MPI 50 MPI 139 MPI 139
System DFT: 100 microns (4 mils)]

[New; MPI INT 9.2B-G5 (Semigloss) / Existing; MPI RIN 9.2B-G5 (Semigloss)
Primer: Intermediate: Topcoat:
MPI 50 MPI 141 MPI 141
System DFT: 100 microns (4 mils)]]

3. [Institutional Low Odor / Low VOC Latex
[New; MPI INT 9.2M-G2 (Flat) / Existing; MPI RIN 9.2M-G2 (Flat)
Primer: Intermediate: Topcoat:
MPI 50 MPI 144 MPI 144
System DFT: 100 microns (4 mils)]

[New; MPI INT 9.2M-G3 (Eggshell) / Existing; MPI RIN 9.2M-G3 (Eggshell)
Primer: Intermediate: Topcoat:
MPI 50 MPI 145 MPI 145
System DFT: 100 microns (4 mils)]

[New; MPI INT 9.2M-G4 (Satin) / Existing; MPI RIN 9.2M-G4 (Satin)
Primer: Intermediate: Topcoat:
MPI 50 MPI 146 MPI 146
System DFT: 100 microns (4 mils)]

[New; MPI INT 9.2M-G5 (Semigloss) / Existing; MPI RIN 9.2M-G5 (Semigloss)
Primer: Intermediate: Topcoat:
MPI 50 MPI 147 MPI 147
System DFT: 100 microns (4 mils)]]

B. New [and Existing, previously painted] [Plaster] [and] [Wallboard] in
[toilets,] [food-preparation,] [food-serving,] [restrooms,] [laundry areas,]
[shower areas,] [areas requiring a high degree of sanitation,] [_____] [and
other high humidity areas] not otherwise specified.:

1. [Waterborne Light Industrial Coating
New; MPI INT 9.2L-G5 (Semigloss) / Existing; MPI RIN 9.2L-G5 (Semigloss)
Primer: Intermediate: Topcoat:
MPI 50 MPI 153 MPI 153
System DFT: 100 microns (4 mils)]

2. [Alkyd
New; MPI INT 9.2C-G5 (Semigloss) / Existing; MPI RIN 9.2C-G5 (Semigloss)
Primer: Intermediate: Topcoat:
MPI 50 MPI 47 MPI 47
System DFT: 100 microns (4 mils)]

3. [Epoxy
New; MPI INT 9.2E-G6 (Gloss) / Existing; MPI RIN 9.2D-G6 (Gloss)
Primer: Intermediate: Topcoat:
MPI 50 MPI 77 MPI 77
System DFT: 100 microns (4 mils)]

-- End of Section --